# FORMULA RECORD

Formula Y-1225

Date 7-15-28 Old No.

Classification

| | X | Lbs. | Gal. | 2 Gal. | Code No. | Percent | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|
| 1 | (a) | | Neutral Mixing | | Y-131 | | Grind |
| 2 | " | | Spar Varnish | | Y-115-A | | Time of Mix |
| 3 | " | | T.P. Rope Impregnat. | | Y-213-A | | Temp. of Oil |
| 4 | 12 | | Ferro Siccat. | | R-21 | | Viscosity |
| 5 | " | | Flint Color | | RC-12 | | Analysis |
| 6 | " | | Putty | | R-11 | | |
| 7 | " | | Turple Yellow | | YR-6 | | |

N12385

GLD060166

# FORMULA RECORD

A 450 5m 5-25

Goods Papalac Enamel-Golden Brown — Formula V-1229-A

Consistency — Date 7-16-25 Old No.

For Use on — Classification

| 1/2 | 6 | 1/2 Bbl | Bbl. | 2 Bbl. | Code No. | Per cent | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|
| 2 | Gal. | Neutral Mixing | | | V-131 | | Grind |
| 2 | " | Spar Varnish | | | V-135-A | | Kind of Mill |
| 4 | " | W.P. Dark Japalac-A | | | V-218-A | | Rate per hr. |
| 4 | lbs. | Burnt Sienna | | | S-21 | | Strainer |
| 3 | " | Burnt Umber | | | BU-17 | | Analysis |
| 4 | " | Pulp | | | W-11 | | |
| 16 | " | Woods Yellow | | | YW-6 | | |

GLD060167

# FORMULA RECORD

A 430 Im 1-28
Printed in U.S.A.

Goods: Japalac Enamel - Golden Brown  Formula No. Y-1229-B

Consistency  Date 8-3-28 Old No.

For Use on  Cost Classification

| 1 | 5 | ½ Bbl | Bbl. | 2 Bbl. | Code No. | Per cent | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|
| 25 | gal. | Neutral Mixing | | | V-131 | | Grind |
| 25 | " | No. 2 Oil | | | V-202-A | | Kind of Mill |
| 43 | " | W. P. Dk. Japalac | | | V-218-A | | Rate per hr. |
| 2 | " | E-Japan | | | D-5 | | Strainer |
| 5 | " | Varnolene | | | S-43 | | Weight per Gallon |
| 50 | lbs. | Burnt Sienna | | | R-21 | | Light Baume Temp. |
| 37 1/2 | " | Burnt Umber | | | BR-17 | | Heavy Baume Temp. |
| 200 | " | Woods Yellow | | | YW-6 | | Viscosity Temp. |
| 50 | " | asbestine Pulp | | | W-11 | | Make of Viscosimeter |
| | | | | | | | Flash Point |
| | | | | | | | Is Agitator Package Required |
| | | | | | | | Remarks |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| | | | | | | | |
| Yield | | | | | | | |

GLD060168

M-47-6M-11-40 PRINTED IN U.S.A. (B CO.)

# COST DEPARTMENT RECORD

Classified Formula No. 4-1229C(N)

Goods JAPALAC ENAMEL-GOLDEN BROWN-(TEMP. RD6) Laboratory Formula No.

Consistency R.M. Date 2-13-41 Factory Letter No. R-071-178

For Use on Production No.

Customer Cost Classification

| Ingredient Code Number | Lab'ty Formula | Large Batch Pounds | Large Batch Gallons | Do not write in these columns For Cost Department Use Only | Manufacturing Specifications |
|---|---|---|---|---|---|
| W-77 | 1 7/8 | 120 | | | Grind "A" |
| BN-17 | 7/8 | 24 | | | Kind of Mill Stone |
| R-21 | 3/4 | 48 | | | Strainer Tinc |
| YW-2 | 7/16 | 28 | | | Weight per Gallon |
| YW-37 | 3/32 | 6 | | | Light Baume Temp. |
| W-11 | 1 1/4 | 80 | | | Heavy Baume Temp. |
| G) V-109 | 3 1/2 | | 28 | | Viscosity 127 1/2" Temp 80° |
| V-119 | 1 1/2 | | 12 | | Viscosimeter #4 Ford |
| V-706 | 2 | | 16 | | Flash Point |
| RVL-1191 | 1 | | 8 | | Is Agitator Required |
| VM-430 | 3/32 | | 3/4 | | |
| 8742 | Trace | | | | Formulator J. FRYCE |
| Yield | | | | | |

GLD060170

N-47 SM 11-40 PRINTED IN U.S.A. (B CO.)

# COST DEPARTMENT RECORD

Classified Formula No. 4-1219 D (RM)

Goods JAPALAC ENAMEL - GOLDEN BROWN

Laboratory Formula No.

Consistency R.M. Date 6-12-41

Factory Letter No. R-061-021

For Use on

Production No.

Customer

Cost Classification

| Ingredient Code Number | Lab'ry Formula | Large Batch: Pounds | Large Batch: Gallons | Do not write in these columns For Cost Department Use Only | | | | | | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|---|---|---|
| R-21 | 11½ | 96 | | | | | | | | Grind "A" |
| BN-17 | 3/4 | 48 | | | | | | | | Kind of Mill Stone |
| 4W-2 | 13/32 | 70 | | | | | | | | Strainer Fine |
| 167-9206 | ½ | 32 | | | | | | | | Weight per Gallon |
| W-91 | 3/4 | 48 | | | | | | | | Light Baume Temp |
| W-11 | ¼ | 16 | | | | | | | | Heavy Baume Temp |
| VM-308 | 1/16 | 4 | | | | | | | | Viscosity 1150" Temp 80° |
| G) V-850 | 3¾ | | 30 | | | | | | | Viscosimeter #4 Ford |
| V-318 | 3¾ | | 30 | | | | | | | Flash Point |
| S-43 | ½ | | 4 | | | | | | | Is Agitator Required |
| D-29 | 1/8 | | 1 | | | | | | | |
| D-44 | 1/16 | | ½ | | | | | | | Formulator J. FRYCE |
| Yield | | | | | | | | | | |

GLD060171

490-2 SOM 6-40 PRINTED IN U.S.A. (WP)

# FORMULA RECORD

Goods Spatter Enamel Golden Brown Formula No. V1249

Consistency Enamel Date 4/24/41 Laboratory No.

For Use on Cost Classification

| Code Number | One Gallon Batch | | | Gallon Batch | | | Gallon Batch | | | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|---|---|---|
| | Pints | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | |
| 6397 | | | 14 | 57 | | | | | | Grind R. |
| 8423 | | | 2 | 1 | | | | | | Kind of Mill Stone |
| V316 | | 2 | 4 | 1 | | | | | | Strainer |
| 1011 | | | 8 | 1 | | | | | | Weight per Gallon 9 lbs 2 |
| V308 | | | 1 | 1 cut | | | | | | Light Baume Temp. |
| | | | | | | | | | | Heavy Baume Temp. |
| V273 | 3¾ | | | | | | | | | Viscosity 110 Temp. |
| V312 | 3¾ | | | | | | | | | Viscosimeter |
| 5423 | ½ | | | | | | | | | Flash Point |
| | | | | | | | | | | Is Agitator Required |
| 4429 | | | 2 | 2 lbs 4 oz | | | | | | Remarks Harvard |
| 8423 | | | 1 | " " | | | | | | Blue |
| | | | | | | | | | | 1 PW |
| | | Changed to new Master Formula | | | | | | | | |
| | | | | | 11 | 4 | 6 | | | Mix Porcelain |
| Bond in V850 | | | | | | | | | | Panel |
| | | | | | | | | | | |
| | | | | | | | | | | |
| Yield | | | | | | | | | | |

DISCONTINUED SEE 11-7-41

GLD060172

N-47 SM 11-49 PRINTED IN U.S.A. (B CO.)

# COST DEPARTMENT RECORD

Goods: Jafalac Chemical Golden Banana (Rdy) — Classified Formula No. 404

Consistency: — Date: 4/24/52 — Laboratory Formula No. 2 TEMP.

For Use on: — Factory Letter No. P-032-052

Customer: — Production No.

Cost Classification

| Ingredient Code Number | Lab'ty Formula | Large Batch Pounds | Large Batch Gallons | Do not write in these columns For Cost Department Use Only | Manufacturing Specifications |
|---|---|---|---|---|---|
| YW-2 | | 32 | | | Grind "A" |
| R-21 | | 48 | | | Kind of Mill STONE |
| BN-17 | | 16 | | | Strainer |
| W-77 | | 48 | | | Weight per Gallon 10# |
| YW-37 | | 8 | | | Light Baume Temp. |
| W-11 | | 32 | | | Heavy Baume Temp. |
| W-10 | | 64 | | | Viscosity 140" ± 5" Temp. |
| 2-KB-74 | | | 44 | | Viscosimeter |
| RVL-123 | | | 16 | | Flash Point |
| S-13 | | | 4 | | Is Agitator Required |
| D-40 | | | 3/4 | | |
| CH-189 SUB. | | | 12 L.D. | | Formulator Schaffer |
| Yield | | | | | |

GLD060173

4800 25M 1-41 PRINTED IN U.S.A. WPI

# FORMULA RECORD

Goods JAP-A-LAC ENAMEL GOLDEN BROWN Formula No. Y 1229 G

Consistency Date 9-26-41 Laboratory No.

For Use on Cost Classification

| Code Number | One Gallon Batch | | | Gallon Batch | | | Gallon Batch | | | Manufacturing Specification |
|---|---|---|---|---|---|---|---|---|---|---|
| | Pints | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | |
| R 237 | | | 14 | | | | | | | Grind A |
| BN 23 | | | 4 | | | | | | | Kind of Mill STONE |
| YW 6 | | 2 | 4 | | | | | | | Strainer |
| W H | | | 8 | | | | | | | Weight per Gallon 9 1/4# |
| VM 308 | | | 1 | | | | | | | Light Baume Temp. |
| | | | | | | | | | | Heavy Baume Temp. |
| V 706 S | 4 | | | | | | | | | Viscosity 110-120" Temp. |
| V 318 A | 4 | | | | | | | | | Viscosimeter |
| | | | | | | | | | | Flash Point |
| D 29 | | | 2 1/2 OZ TO GAL | | | | | | | Is Agitator Required |
| D 2A | | | 1 " " | | | | | | | Remarks |
| | | | | | | | | | | |
| GRIND IN V 706 S | | | | | | | | | | MATCH PORCELAIN PANEL |
| CHANGED BECAUSE V 550 NOT AVAILABLE | | | | | | | | | | |
| | | | | | | | | | | |
| Yield | | | | | | | | | | HAYWARD |

DISCONTINUED

SEE NEXT PAGE

(11/14/41)

GLD060174

MOLD 28M 1-41 PRINTED IN U.S.A. (WP)

# FORMULA RECORD

DISCONTINUED

Goods Japalac Enm. Golden Brown  Formula No. Y1229E

Consistency Liquid  Date 11-19-41  Laboratory No.

For Use on  Cost Classification

| Code Number | One Gallon Batch | | | Gallon Batch | | | Gallon Batch | | | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|---|---|---|
| | Parts | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | |
| R237 | | | 14 | | | | | 2 | | Grind a |
| BR23 | | | 4 | | | Use proper qty | | | | Kind of Mill Stone |
| YW6 | | 2 | 4 | | | | | | | Strainer |
| W11 | | | 8 | | | | | | | Weight per Gallon 9 7/8 |
| VM308 | | | 1 | | | | | | | Light Baume Temp. |
| | | | | | | | | | | Heavy Baume Temp. |
| V706-8 | 4 | | | | | | | | | Viscosity 40-120" Temp. |
| V705-CL | 4 | | | | | | | | | Viscosimeter |
| | | | | | | | | | | Flash Point |
| D29 | | | 2 | Lg. to gal | | | | | | Is Agitator Required |
| D2A | | | 1 | " " | | | | | | Remarks |
| | | | | | | | | | | Hayward |
| | | | | | | | | | | Match Porcelain |
| | | | | DISCONTINUED | | | | | | Panel |
| | | | | SEE Y1229 | | | | | | |
| | | | | 7/12/43 | | | | | | |
| Yield | | | | | | | | | | |

GLD060175

400-O 5014 PRINTED IN U.S.A. (6)

# FORMULA RECORD

Goods [illegible] Formula No. [illegible]

Consistency [illegible] Date [illegible] Laboratory No. [illegible]

For Use on [illegible] Cost Classification

| Code Number | One Gallon Batch | | | Gallon Batch | | | Gallon Batch | | | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|---|---|---|
| | Pints | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | |
| [illegible] | | | [illegible] | | | | | [illegible] | | Grind [illegible] |
| [illegible] | | | [illegible] | | | | | [illegible] | | Kind of Mill [illegible] |
| [illegible] | | [illegible] | [illegible] | | | | | [illegible] | | Strainer |
| [illegible] | | | [illegible] | | | | | [illegible] | | Weight per Gallon [illegible] |
| | | | | | | | | | | Light Baume Temp. |
| [illegible] | [illegible] | | | | | | [illegible] | | | Heavy Baume Temp. |
| [illegible] | [illegible] | | | | | | [illegible] | | | Viscosity [illegible] Temp. |
| [illegible] | [illegible] | | | | | | [illegible] | | | Viscosimeter |
| [illegible] | [illegible] | | | | | | [illegible] | | | Flash Point |
| | | | | | | | | | | Is Agitator Required |
| [illegible] | | | [illegible] | [illegible] | | | [illegible] | | | Remarks |
| [illegible] | | | [illegible] | [illegible] | | | [illegible] | | | [illegible] |
| | | | | | | | | | | [illegible] |
| | [illegible] | | | | | | | | | [illegible] |
| | | | | | | | | | | |
| | | | | | | | | | | |
| | | | | | | | | | | |
| Yield | | | | | | | | | | |

DISCONTINUED
SEE # 1229-Y 3/23/45

GLD060176

480-D SDM 2-44 PRINTED IN U.S.A. (B)

# FORMULA RECORD

Goods Opaline Yellow Brown Enamel  Formula No. 4-1229E

Consistency  Date 3-23-45  Laboratory No.

For Use on  Cost Classification

| Code Number | One Gallon Batch | | | Gallon Batch | | | Gallon Batch | | | Manufacturing Specifications |
|---|---|---|---|---|---|---|---|---|---|---|
| | Pints | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | Gals. | Lbs. | Ozs. | |
| R 237 | | | 14 | | | | | 70 | | Grind A |
| BW 23 | | | 4 | | | | | 20 | | Kind of Mill 3 Roll |
| 4W 6 | | 2 | 4 | | | | | 180 | | Strainer |
| OW 181 | | | 8 | | | | | 40 | | Weight per Gallon 9 1/2 |
| W 104 | | | 2 | | | | | 10 | | Light Baume Temp. |
| | | | | | | | | | | Heavy Baume Temp. |
| V 357 | 1 1/2 | | | | | | 15- | | | Viscosity 86-90 Temp. |
| VR 45016 | 5 3/4 | | | | | | 57 1/2 | | | Viscosimeter |
| 063 | 1/2 | | | | | | 5 | | | Flash Point |
| 543 | 1/4 | | | | | | 2 1/2 | | | Is Agitator Required |
| | | | | | | | | | | Remarks Hayward |
| VM 524 | | 1 | 4 3/4 | | | | 17 1/2 | | | |
| D 13 | | 1 | 2 | | | | 1 1/4 | | | Match Porcelain panel 1.45 oil/gal. |
| replaced 1-29 | | | | | | | | | | |
| | Changed to new Opaline Quality | | | | | | | | | |
| Yield | | | | | | | | | | J.P.W. |

Standard Formula
Not to be taken
from File.

GLD060177

| Characteristics and Method of Using | Cost Data | | | | Customers |
|---|---|---|---|---|---|
| Type of Goods | | | | | |
| Color | | | | | |
| Luster | | | | | |
| Match for | | | | | |
| | | | | | |
| Kind of Reducer | | | | | |
| Amount of Reduction for | | | | | |
| Brushing | | | | | |
| Spraying Pressure | | | | | Aeroplanes 3-29-45 |
| Dipping Drip Time | Analysis | | | | |
| Flocoing Drip Time | Pigments | | | | 34.5% Toronto 8/27/4 |
| Tumbling | Titanated Pigment | | | 21.9% | |
| Air dry to recoat | Iron Oxide Red | | | 6.2% | |
| To Sand or Rub | Phthalic Alkyd | | | 56.4% | |
| Bake Time Temp. | Mineral Spirits | | | 12.1% | |
| Rub with | Lead Co Naphthenate | | | 3.4% | |
| Polish with | | | | 100.0% | |
| Schedule | Vehicle | | | 65.5% | |
| | Phthalic Alkyd | | | 26.9% | |
| | Petroleum Oil | | | 4.6% | |
| | Mineral Spirits | | | 2.7% | |
| | Liquid Driers | | | 2.8% | |
| | | | | 100.0% | |
| | | | | | |
| | | | | | |

GLD060178