

FILE NAME: Talc (TALC)

DATE: 1956 Oct 8

DOC#: TALC408

DOCUMENT DESCRIPTION: Memo RE Particle Size Distribution of
J-M Talc

Johns-Manville Research Center

Report No. 412-T-467 CONFIDENTIAL

Date October 8, 1956

Title: PARTICLE SIZE DISTRIBUTION OF JOHNS-MANVILLE TALC

Requested by: C. Sheckler, Manville Plant

SUMMARY

A sample of powdered talc, supplied by Eastern Magnesia Talc Company and used by Johns-Manville Corporation, was submitted for a determination of particle size distribution. Distribution was determined by the Klein Hydrometer method in isopropyl alcohol using 5 per cent Triton X-100 as a dispersant. The results of the determination are as follows:

>20 microns	35 % weight
20-10 microns	63 % weight
10-8 microns	0.5% weight
8-6 microns	0.4% weight
<6 microns	1.1% weight

Contents: Summary only.

Approved by:

H. L. King
H. L. King

Reported by:

F. L. Kadey, Jr.
F. L. Kadey, Jr.

cc: C. F. Bassweiler, CH
C. Sheckler, Manville (3)
E. R. Williams
A. B. Cummins
H. L. King
File: 412 (7)