December 8. 1961

PYDRAUL A-200

Use the following measurements and weights for making Pydraul A-200.

8,000 Gal. Batch

Aroclor 1242 to 117" outage as measured in #1 mix tank
Aroclor 1248 to 60" outage as measured in #1 mix tank

Santolube 393 - 500 lbs.
Santolube 70 - 500 lbs.
Dow Corning 200 Fluid - 5 lbs.

Blue A Dye 318 grams
Azo Oil Black 91 grams

12,000 Gal. Batch

Aroclor 1242 to 103" outage as measured in #1 mix tank
Aroclor 1248 to 20" outage as measured in #1 mix tank

Santolube 393 750 lbs.
Santolube 70 750 lbs.
Dow Corning 200 Fluid 7½ lbs.

Blue A Dye 477 grams
Azo Oil Black 136 grams

R. Smith



0000534