Organic Chemicals

RECEIVED
MONSANTO
MONSANTO CHEMICAL COMPANY
INFORMATION CENTER
ST. LOUIS

MONSANTO TERPHENYLS

Monsanto Technical Bulletin No. O-127
Reprinted January 1, 1956
Organic Chemicals Division
Monsanto Chemical Company - St. Louis, Missouri

MONSANTO TERPHENYLS

The Monsanto TERPEHNYLS are a series of hydrocarbon solids ranging in melting point from a little above room temperature to as high as 210° C. (410°F.).

Monsanto TERPHENYLS have found use as plasticizers, softening agents, wax additives and extenders, and in paper coatings. Various properties of the TERPHENYLS are presented in this bulletin to facilitate the selection of the proper one for specific applications.

The information contained in this bulletin is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. The Monsanto Chemical Company disclaims any liability incurred in connection with the use of these data or suggestions.

Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

MONSANTO TERPHENYLS - Monsanto Technical Bulletin No. O-127
January 1, 1956

0615138

TOWOLDMON0039210
WATER_PCB-00023679

PHYSICAL PROPERTIES

	Ortho	Meta	Para
Formula:			
Color - NPA:	<1.5	<3.5	<2.0
Density - g./cc.:	1.14	1.164	1.236
Melting Point:			
Completely liquid	55°C. (131°F.)	90°C. (194°F.)	213°C. (415°F.)
Solidification Temp.:			
First crystals	--	<90°C. (<194°F.)	209-213°C. (408-415°F.)
Hold point	53-55°C. (127-131°F.)	83-85°C. (181-185°F.)	--
Distillation Range: D-20 corrected	330-350°C. (626-662°F.)	368-378°C. (694-712°F.)	381-388°C. (718-730°F.)
Flash Point:	171°C. (340°F.)	207°C. (405°F.)	207°C. (405°F.)
Flame Point:	193°C. (390°F.)	229°C. (445°F.)	238°C. (460°F.)
Viscosity S.U.S. at 210°F.:	40.6 (See Graph No. I)	39.3	28.8 (at 225°C.)
Solubility:	See Graphs Nos. II, III and IV		

0615139

TOWOLDMON0039211
WATER_PCB-00023680

Vapor Pressure (mm. of Mercury):

T°C.	Ortho	Meta	Para	
90	0.17	-	-	
100	0.3	-	-	
110	0.5	0.15	-	
120	0.9	0.3	-	
130	1.5	0.5	-	
140	2.4	0.8	0.15	
150	3.7	1.3	0.3	
160	5.7	2.0	0.6	
170	8.2	3.0	1.0	
180	12.0	4.6	1.9	Solid
190	18.0	6.8	3.2	
200	25.0	9.8	5.5	
210	35.0	14.0	9.1	
220	46.0	19.0	14.0	
230	62.0	26.0	19.0	
240	82.0	36.0	26.0	
250	110.0	48.0	35.0	
260	140.0	63.0	46.0	
270	180.0	83.0	61.0	
280	230.0	110.0	80.0	
290	290.0	140.0	101.0	
300	360.0	180.0	130.0	
310	450.0	220.0	165.0	
320	550.0	270.0	210.0	
330	670.0	340.0	260.0	
340	810.0	410.0	320.0	
350	990.0	500.0	390.0	
360	1160.0	610.0	470.0	
370	1390.0	730.0	570.0	
380	1600.0	870.0	680.0	

ELECTRICAL PROPERTIES

Terphenyl	Dielectric Constant	Resistivity - ohm-cm. 100°C.	250°C.
Ortho	2.54	8200 X 10^9	-
Meta	2.62	2600 X 10^9	-
Para	-	-	30 X 10^9

STABILITY

No detectible effect on boiling Terphenyls in 10% Sulfuric Acid or Caustic Soda.

0615140

TOWOLDMON0039212
WATER_PCB-00023681

COMPATIBILITY

Ortho Terphenyl / Other Component	% Ortho Terphenyl in Mixture 10	25	50	75	90
Paraffin (120°/125°F.)	C		C		C
Barnsdall (160°/165°F.)	C		C		C
Beeswax	C	C	C		I
Opal Wax	C		I		I
Stearic Acid	I	I	I		I
"N" Wood Rosin	C	C	I	I	

Meta Terphenyl / Other Component	% Meta Terphenyl in Mixture 10	25	50	75	90
Paraffin (120°/125°F.)	Incompatible with 2% or more Meta Terphenyl				
Barnsdall Wax (160°/165°F.)		C	B	I	I
Ceresin	I		I		I
Carnauba Wax	C		C	C	I
Candelilla Wax	C	C	I		I
Montan Wax	I		I		I
Beeswax	I		I		I
Japan Wax	C	I	I		
Opal Wax	C	C	I		I
I. G. Wax O	I		I		I
Stroba Wax	I		I		I
Acra Wax	C		C		B
Stearic Acid	I		I		I
Shellac	C		I		I
Manila Resin (Loba B)	C		I		I
Ester Gum	C		I		I
"N" Wood Rosin (Hercules)	C	C	I		I
Piccolite Resin (85°)	C		I		I
Staybellite Resin	B		I		I

Para Terphenyl / Other Component	% Para Terphenyl in Mixture 0.5	1-2	3	5	10-75
Paraffin (120°/125°F.)	I				
Paradene No. 1				C	I
Paradene No. 2		C	I		
"N" Wood Rosin					I

Note: C = Compatible
I = Incompatible
B = Almost Compatible

0615141

TOWOLDMON0039213
WATER_PCB-00023682

COMPARATIVE HARDNESS

(Smaller values denote greater hardness)

Material	Average Penetration in cm. x 10^{-2} in 60 seconds at 25°C. under load indicated (ASTM D-5-25) 50 Grams	150 Grams	250 Grams
Meta Terphenyl	0	0	2.3
Para Terphenyl	0	0	3.3
Carnauba Wax	0	2.3	4.7
Candelilla Wax	0	3.3	4.7
Ortho Terphenyl	1.3	4.0	10.7
50% Paraffin & 50% Meta Terphenyl	3.7	12.3	18.0
75% Paraffin & 25% Meta Terphenyl	7.3	18.0	25.3
Ceresin Wax	9.3	15.7	26.0
95% Paraffin & 5% Meta Terphenyl	10.7	21.0	29.7
98% Paraffin & 2% Meta Terphenyl	11.7	26.0	32.7
Paraffin Wax	14.3	23.3	31.3
Montan Wax	15.0	28.7	37.3
Mixed Isomeric Terphenyl			
No aging	60.0	-	-
Aged 24 hours	28.7	-	-

AVAILABILITY

The Terphenyls are available in limited quantities.

0615142

TOWOLDMON0039214
WATER_PCB-00023683



TOWOLDMON0039215
WATER_PCB-00023684

Graph II - SOLUBILITY OF ORTHO TERPHENYL



TOWOLDMON0039216
WATER_PCB-00023685



TOWOLDMON0039217
WATER_PCB-00023686

Graph IV - SOLUBILITY OF PARA TERPHENYL



TOWOLDMON0039218
WATER_PCB-00023687



For further information about Monsanto TERPHENYLS contact the nearest Monsanto office.

MONSANTO CHEMICAL COMPANY

St. Louis

Akron . Atlanta . Boston . Chicago . Cincinnati

Cleveland . Detroit . Houston . Los Angeles

Minneapolis . New York . San Francisco . Seattle

Wilmington . Monsanto Chemicals Ltd. (London)

Monsanto Chemicals Ltd. (Australia)
Melbourne

Monsanto (Canada) Ltd.
Montreal . Toronto . Vancouver

Representatives in the Principal Cities of the World.

0615147

TOWOLDMON0039219
WATER_PCB-00023688