CG 03 CODE KY-908-D PKG ____ PROCESSES: KY-908-D (G) APPROVED BY FWP 06/30/82

LOT L2J16 NOV 3 1982

EST. WT. 4226* LBS.

MAKING NOTES _____

JOB NAME: 03KY908DPG

INSTRUCTIONS	= PRESSING =	RECORD				
VAT 244	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE 11-4-82	STARTED	1021				
TIME 10:30 A.M.	CAKES USED	4m				
RELEASED BY	WATER ON	4/6				
PRESS 21 | 22 | 23 | 24	HRS. WASHED	4				
NO. OF CAKES 46 | 46 | 46 | 52	M MHOS	172				
PRESS WITH AGITATION	HRS. WASHED					
WASH TO 500 M MHOS - 135-145 F WATER	M MHOS					
TEST AFTER 2 HOURS	HRS. WASHED					
LOAD ON 7 CARS	M MHOS					
	CAKE CONDITION					
	NO. CARS LOADED	7				
	EXPLAIN LOSSES					
SAMPLES	SAMPLED BY					
DELIVER TO	RELEASED BY					

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED 1

NO DRUMS 15

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

LUMP WGT 4269

= GRINDING =

MILL 939 HSP 3/32"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO QTL

DATE MIXED

SAMPLED BY
RELEASED BY

16
41
371

0.00 *

3.02 +
0.12 -
3.03 +
0.12 -
3.10 +
0.12 -
2.99 +
0.12 -
3.05 +
0.12 -
2.97 +
0.12 -
3.06 +
0.12 -
3.02 +
0.12 -
2.86 +
0.12 -
2.90 +
0.12 -
3.05 +
0.12 -
3.12 +
0.12 -
2.88 +
0.12 -
3.15 +
0.12 -
2.29 +
0.12 -
42.69 *

7 cm

DUP050059911