

LOT MAY -0-81-E 1439

ALTERNATE

TYPED BY JMH

EST'D WGT 5632

MAKING NOTES

TOTAL EST'D WGT= LBS (CRT ENTRY)

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 92 93
NO. OF CAKES 54 54 54
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED 6
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 5716

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

RPM SCREEN
MAX. TEMP.
F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1439
41
231

0.00 *

3.45 +
0.12 -
3.41 +
0.12 -
3.47 +
0.12 -
3.33 +
0.12 -
3.38 +
0.12 -
3.29 +
0.12 -
3.25 +
0.12 -
3.27 +
0.12 -
3.44 +
0.12 -
2.99 +
0.12 -
3.30 +
0.12 -
3.37 +
0.12 -
3.02 +
0.12 -
3.76 +
0.12 -
45.05

45.05 +
3.26 +
0.14 -
3.31 +
0.14 -
3.24 +
0.14 -
2.86 +
0.14 -
57.16 *