

CKR INDUSTRIES INC

08-09-83 09:40 ID:KG OVERSEAS-DEPT0575 TEL NO:81-472-56-8575
 08/09/83 14:28 ADEKA ARGUS CHEMICAL

MS39 P06
 P04

Typical Formulation of (I)

PVC (K.V=70)	100
DIDP or DL-911P	70
ADK Ciser O-130S	3.0
CaCO ₃	20
CPS-1	2.0
1500 or 1505A	0.5

Typical Formulations (II) and (III)

The transparent PVC layer

PVC (K.V=70)	100
DIDP or DL-911P	70
ADK Ciser O-130S	3
AC-183	1.0
(Liquid Ba/Zn)	
CPS-1	1.0
1178	0.5
(Chalator)	

The opaque PVC layer

PVC (K.V=70)	100
DIDP or DL-911P	90
ADK Ciser O-130S	3
CaCO ₃	20
CPS-1	2.0
1500 or 1505A	0.5-1.0

(III) Typical Formulation for extrusion PVC Automotive Side-Mold

PVC (K.V=65)	100
DIDP or DL-911P	50
EP-13	1.0
(Epoxy Resin Type)	
AC-190	1.0
(Liquid Ba/Zn)	
CPS-1	1.0
1500 or 1505A	0.5

The information contained herein is accurate to our best knowledge, but Adeka Argus Chemical Co. makes no warranties, express or implied, for any advice furnished by it or results obtained with respect to its products. Any liability in connection with the use by others of the information, recommendations or suggestions herein is disclaimed. Furthermore, nothing contained in this publication shall be construed as a license to operate under or as a recommendation to infringe any patents "Argus," MARK, DRAPEX and AIN CIXEN are registered trademarks of Adeka Argus Chemical Co., Ltd.

CHARDO 02025