MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-907D LOT K2K65

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	96	4800		
	Lump STUMP	4678		

TOTAL NET WT. 4800 PKG. N–CODE 1000

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	10/25	

PRODUCT NAME = KROLOR YELLOW - MEDIUM NON-BLEEDING 2/23/82

CG 03 CODE KY-907-D PKG ____

PROCESSES: KY-907-D (H)

APPROVED BY FWP 12/19/82

LOT **K2K65** OCT 15 1982

22/244

TYPED BY KLW

MAKING NOTES _____

EST. WT. 4780* LBS.

JOB NAME: 03KY907DPH

E.C.

= PRESSING =

INSTRUCTIONS					
VAT	244				
DATE	10-29				
TIME	11:15A				
RELEASED BY	237				
PRESS	2	22	23	24	95
NO.OF CAKES	46	46	46	52	

PRESS WITH AGITATION

WASH TO 500 M MHOS - 135-145 F WATER

TEST AFTER 3 HOURS

LOAD ON 8 CARS

SAMPLES

DELIVER TO

RECORD	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED	1145				
CAKES USED	52				
WATER ON	5A				
HRS. WASHED	5				
M MHOS	159				
HRS. WASHED					
M MHOS					
HRS. WASHED					
M MHOS					
CAKE CONDITION					
NO CARS LOADED	7				

EXPLAIN LOSSES

SAMPLED BY

RELEASED BY BLL

= DRYING =

DRY 24 HOURS AT 180 F

NOTE: DRY ON FIRST STAGE ONLY.

RE-SET ON FIRST STAGE TIL DRY.

SAMPLES

DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATD

cannot account for low yield.

No record of any process losses.

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 15

LUMP WGT 4678

NO CARS PULLED

SAMPLED BY

RELEASED BY A.K.

= GRINDING =

MILL 939 HSP 3/32"RP SCREEN 3500 RPM

MAX. TEMP. 170 F

SAMPLE W/O MIXING 1 ENV & 2 PT CANS

IF PACKED IN BAGS SAMPLE AS FOLLOWS:

FIRST BAG: 1 ENV.

40TH BAG: 1 ENV. & 2 PINT CANS

LAST BAG: 1 ENV.

DELIVER TO OTL

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050102624



DUP050102625