MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-788 LOT 34875

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	67	3,350		
	STUMP			

TOTAL NET WT. 3,350 PKG. N–CODE 1280

PROD. SPVR. DATE WHSE. OPER.

3/16/80

22
12244 CG 03 CODE KY-788-D PKG. ____

→ MAR 14 34875

EST. WGT. 960 860 LBS.

OK. TP

O-K BAGS

3460

Total Wgt. 3560# Req(____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/27/76
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT — NON-BLEEDING

INSTRUCTIONS

VAT		2HH			
DATE		3/14/80			
TIME		12:30 AM			
RELEASED BY		KKR			
PRESS	22	23	24		
NO. OF CAKES	46	46	46		

PRESS With AGITATION
WASH TO 2000 OHMS with 35-75°F water
TEST AFTER 2 HOURS
LOAD on 6 cars

J.K.

SAMPLES 1- 8oz JAR
DELIVER TO CTL for Color

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1:30 AM				
CAKES USED	216				
WATER ON	5:30 AM				
HRS. WASHED	3				
OHMS	2200				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	G				
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY 382 RELEASED BY

-DRYING-

Dry 12 hrs at 220 °F L.V. H.V.
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums 13

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3376
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

DUP050094652

.00 T

.00 T

348.75 #
-.41 #
.16 #
.00 T

2.45
.12 -
2.45
.12 -
2.40
.12 -
2.39
.12 -
2.42
.12 -
2.51
.12 -
2.52
.12 -
2.41
.12 -
2.45
.12 -
2.46
.12 -
2.49
.12 -
2.47
.12 -
2.35
.12 -
2.37
.12 -
1.42
.12 -
33.76 T

DUP050094653