MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE ~~KO-786~~ LOT ~~33600~~

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
~~2514~~	~~1~~	~~T. 44~~		
~~2390~~	~~1~~	~~T. 147~~		
STUMP				

TOTAL NET WT. ~~4904~~ PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
~~SMH~~	~~1/6/80~~	

N28575

DUP050095143

2/5/76

CG 04 CODE KO-786-D PKG. ____

→ JAN-3 33600

EST. WGT. 862 LBS.

OK — AP

TOTAL WEIGHT 4962 (Req. ____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KO-786-D (P)	EWK 9-21-76
	DCG 9-21-76
TYPED BY	
jlc 11-15-76	

MAKING NOTES

REMARKS

NAME: "KROLOR" ORANGE R — NON-BLEEDING

INSTRUCTIONS				-PRESSING- RECORD					
VAT	#246			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-2-80 SA			STARTED	2:30 PM				
TIME	6:00 P			CAKES USED	46				
RELEASED BY	C. M			WATER ON	12 Hours				
PRESS	22	23	24	HRS. WASHED	8				
NO. OF CAKES	46	46	52	OHMS	5000				
PRESS with AGITATION				HRS. WASHED					
WASH TO 5000 OHMS with 35-25°F water				OHMS					
TEST AFTER 6 HOURS				HRS. WASHED					
LOAD on 6 cars				OHMS					
				CAKE CONDITION	5				
				NO. CARS LOADED					
				EXPLAIN LOSSES					

SAMPLES 1-8 oz. Jar
DELIVER TO CTL for color

SAMPLED BY RELEASED BY

-DRYING-

HOURS 16 HOURS AT 220°F L.V. I.V.	LUMP: - OK - WET - SALTS - CONTAMINATED
TEMP. °F °F	
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS: 14
SAMPLES	NO. CARS PULLED LUMP WGT. 4959
DELIVER TO	SAMPLED BY RELEASED BY EH

-GRINDING-

MILL 938 HSP 3/32" RF SCREEN 3500 RPM	SCREEN RPM
MAX. TEMP. 210 °F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE AFTER / WITHOUT MIXING	DATE MIXED
SAMPLES 1 Env. + 1 Pint Can	
DELIVER TO CTL	SAMPLED BY RELEASED BY

DUP050095144

33600
41
159

0.00 *

4.03 +
0.12 -
3.88 +
0.12 -
3.68 +
0.12 -
3.80 +
0.12
3.95 +
0.12 -
3.98 +
0.12 -
3.75 +
0.12 -
3.77 +
0.12 -
3.73 +
0.12 -
3.75 +
0.12 -
3.76 +
0.12
3.62 +
0.12
3.54 +
0.12 -
2.13 +
0.12 -
49.59 *

DUP050095145