

RESIDUAL VC1 CONTENT OF FINISHED PVC PRODUCTS

Data Expressed in PPM VC1

PLANT: AVON LAKE

<u>Resin Type</u>	<u>No. Data Points</u>	<u>Average</u>	<u>High</u>	<u>Low</u>
WEEK ENDING: <u>1/24/75</u>				
G-92	14	5.8	33.6	0.5
102EP F-5	24	1.1	6.0	0.1
103EP F-76	28	5.9	17.5	0.3
121	14	6.8	55.9	0.0
124 F-1	4	12.1	31.3	0.9
WEEK ENDING: <u>1/31/75</u>				
102EP F-5	8	0.8	1.5	0.2
103EP F-76	11	6.2	27.8	0.3
110X400	8	10.1	49.2	0.4
WEEK ENDING: <u>2/7/75</u>				
G-92	14	11.5	88.5	0.2
102EP F-5	4	0.4	0.9	0.2
103EP F-76	59	5.7	35.7	0.1
121	5	0.3	0.5	0.1
124	4	1.4	2.6	0.1
WEEK ENDING: <u>2/14/75</u>				
G-92	1	222.0	222.0	222.0
102EP F-5	14	28.2	206.0	0.4
103EP F-76	59	7.0	76.1	0.9
110X334	2	1.7	2.3	1.1
121	2	0.5	0.6	0.5
124	4	2.6	5.0	0.1
WEEK ENDING: <u>2/21/75</u>				
G-92	12	41.9	262.0	0.2
102EP F-5	9	9.0	40.5	0.8
103EP F-76	38	12.5	61.8	0.7
110X340	1	0.4	0.4	0.4
124	6	2.2	4.5	0.1

GDS/clg
2/26/75

BFG13632

21411001

RESIDUAL VC1 CONTENT OF FINISHED PVC PRODUCTS

Data Expressed in PPM VC1

PLANT: AVON LAKE

<u>Resin Type</u>	<u>No. Data Points</u>	<u>Average</u>	<u>High</u>	<u>Low</u>
WEEK ENDING: <u>2/28/75</u>				
G-92	17	4.9	26.4	0.1
102EP F-5	7	4.2	8.1	0.4
103EP F-76	27	9.7	29.6	2.0
110X334	8	6.2	8.9	0.1
110X400	1	0.0	0.0	0.0
121	3	4.3	9.1	0.2
124	6	2.8	10.7	0.2
126	1	0.4	0.4	0.4

BFG13633

21411002

RESIDUAL VCl CONTENT OF FINISHED PVC PRODUCTS

Data Expressed in PPM VCl

PLANT: HENRY

<u>Resin Type</u>	<u>No. Data Points</u>	<u>Average</u>	<u>High</u>	<u>Low</u>
WEEK ENDING: <u>1/24/75</u>				
102EP F-5	8	41.0	120.0	0.0
103EP F-76	8	24.0	43.0	0.0
120X271	1	20.0	20.0	20.0
128	4	27.0	50.0	0.0
WEEK ENDING: <u>1/31/75</u>				
102EP F-5	2	22.0	32.0	12.0
103EP F-76	9	17.0	42.0	10.0
128	1	34.0	34.0	34.0
128 F-1	3	83.0	140.0	36.0
WEEK ENDING: <u>2/7/75</u>				
102EP F-5	2	12.0	12.0	11.0
103EP F-76	2	9.0	13.0	4.0
128	6	50.0	120.0	13.0
128 F-1	1	48.0	48.0	48.0
WEEK ENDING: <u>2/14/75</u>				
102EP F-5	6	0.1	0.1	0.0
103EP F-76	6	3.7	13.0	0.4
128	2	8.3	15.0	1.6
WEEK ENDING: <u>2/21/75</u>				
102EP F-5	7	0.2	0.4	0.1
121	4	14.4	22.6	11.0
128	1	11.4	11.4	11.4
WEEK ENDING: <u>2/28/75</u>				
102EP F-5	10	0.1	0.2	0.1
103EP F-76	2	2.1	3.5	0.4
121	5	8.8	14.2	0.5

GDS/clg
2/26/75

BFG13634

21411003

RESIDUAL VC1 CONTENT OF FINISHED PVC PRODUCTS

Data Expressed in PPM VC1

PLANT: LONG BEACH

<u>Resin Type</u>	<u>No. Data Points</u>	<u>Average</u>	<u>High</u>	<u>Low</u>
WEEK ENDING: <u>1/24/75</u>				
103EP	1	1.0	1.0	1.0
103EP F-76	8	12.0	19.0	4.0
WEEK ENDING: <u>1/31/75</u>				
103EP	1	22.0	22.0	22.0
103EP F-76	11	17.8	26.0	8.0
WEEK ENDING: <u>2/7/75</u>				
102EP F-5	1	23.0	23.0	23.0
103EP	2	13.5	17.0	10.0
103EP F-76	10	17.6	32.0	7.0
WEEK ENDING: <u>2/14/75</u>				
103EP	1	11.0	11.0	11.0
103EP F-76	10	18.1	70.0	4.0
WEEK ENDING: <u>2/21/75</u>				
103EP F-76	16	7.4	22.0	1.0
WEEK ENDING: <u>2/28/75</u>				
103EP	1	2.0	2.0	2.0
103EP F-76	25	11.9	27.0	5.0

GDS/clb
2/26/75

BFG13635

21411004

RESIDUAL VC1 CONTENT OF FINISHED PVC PRODUCTS

Data Expressed in PPM VC1

PLANT: LOUISVILLE

<u>Resin Type</u>	<u>No. Data Points</u>	<u>Average</u>	<u>High</u>	<u>Low</u>
WEEK ENDING: <u>1/24/75</u>				
G-92	4	1.2	3.0	0.0
103EP	15	206.0	538.0	3.0
121	1	1.0	1.0	1.0
135	7	1.6	2.0	1.0
202	2	2642.0	3503.0	1781.0
300X6	4	24.2	41.0	8.0
603X560	10	0.0	0.0	0.0

WEEK ENDING: <u>1/31/75</u>				
G-92	4	0.3	1.0	0.0
103EP	19	151.9	374.0	7.0
103EP F-76	4	101.5	171.0	32.0
110X236	2	2.5	3.0	2.0
126	2	2.5	3.0	2.0
135	2	2.5	3.0	2.0
300X6	1	7.0	7.0	7.0
603X560	3	0.0	0.0	0.0
605X560	7	0.0	0.0	0.0

WEEK ENDING: <u>2/7/75</u>				
G-92	3	0.3	1.0	0.0
103EP	4	84.0	174.0	0.0
103EP F-76	3	136.0	169.0	101.0
121	1	8.0	8.0	8.0
135	2	1.5	2.0	1.0
300X6	1	23.0	23.0	23.0
605X560	4	0.0	0.0	0.0

WEEK ENDING: <u>2/14/75 and 2/21/75</u>				
G-92	9	2.0	6.0	0.0
103EP	21	70.0	317.0	0.0
103EP F-76	8	74.0	171.0	4.0
110X339	1	75.0	75.0	75.0
121	11	12.0	27.0	1.0
126	1	5.0	5.0	5.0
135	1	1.0	1.0	1.0
300X6	1	41.0	41.0	41.0
603X560	15	3.0	9.0	0.0

GDS/clb
2/26/75

BFG13636

21411005

RESIDUAL VC1 CONTENT OF FINISHED PVC PRODUCTS

Data Expressed in PPM VC1

PLANT: LOUISVILLE

<u>Resin Type</u>	<u>No. Data Points</u>	<u>Average</u>	<u>High</u>	<u>Low</u>
WEEK ENDING: <u>2/28/75</u>				
G-92	5	0.8	3.0	0.0
103EP	9	95.6	277.0	2.0
103EP F-76	7	37.9	139.0	5.0
103X24	4	4.0	6.0	2.0
300X6	5	44.2	166.0	5.0
603X560	6	0.8	1.0	0.0

21411006

BFG13637

RESIDUAL VC1 CONTENT OF FINISHED PVC PRODUCTS

Data Expressed in PPM VC1

PLANT: PEDRICKTOWN

<u>Resin Type</u>	<u>No. Data Points</u>	<u>Average</u>	<u>High</u>	<u>Low</u>
WEEK ENDING: <u>1/24/75</u>				
103EP	4	6.8	15.6	2.5
WEEK ENDING: <u>1/31/75</u>				
102EP F-5	1	0.7	0.7	0.7
103EP	4	7.2	15.6	2.5
120X251	1	4.2	4.2	4.2
WEEK ENDING: <u>2/7/75</u>				
80X3	3	2.9	3.6	2.4
102EP F-5	1	2.8	2.8	2.8
103EP	5	7.0	11.4	3.8
120X251	4	17.9	25.5	8.7
WEEK ENDING: <u>2/14/75</u>				
80X3	2	1.3	1.9	0.7
103EP	4	19.1	29.8	1.3
103EP F-76	4	27.8	52.0	2.7
120X241	1	62.9	62.9	62.9
WEEK ENDING: <u>2/21/75</u>				
80X5	1	1.8	1.8	1.8
80X25	1	176.0	176.0	176.0
103EP	3	0.8	1.1	0.5
120X241	1	87.0	87.0	87.0
WEEK ENDING: <u>2/28/75</u>				
80X5	2	2.4	2.7	2.1
103EP	6	2.9	10.1	0.2
121	5	10.5	21.7	4.9

GDS/cl's
2/26/75

BFG13638

21411007