

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE RT870 LOT A2J39

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

17 2588 5STUMP Lump 2578TOTAL NET WT. 2588 PKG. N-CODEOD. SPVR. [Signature] DATE 1/29 WHSE. OPER. 213

NON-BLEEDING

PROCESSES APPROVED BY
RT-878-D (H) EWK 4/7/82

1/13/82

EST. WT 2578# LBS.

TYPED BY JKH
MAKING NOTES INSTRUCT MAKING AREA
TO ADD 10# N-588-A HALFWAY THRU
PRESSING

JOB NAME: 32RT879DFF

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS
NO. OF Cakes
PRESS WITHOUT AGITATION
WASH TO 333 M MHOS - 35-75 F WATER
TEST AFTER 4 HOURS
LOAD ON 11 CARS
PRESS IMMEDIATELY CODE
INSTRUCT MAKING AREA TO ADD 10#
N-588-A HALF-WAY THRU PRESSING.
CLEAN MAGNETIC SEPARATOR AFTER
PRESSING. CLEANED BY: _____

	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED	11:AM	9-PM			
CAKES USED	60				
WATER ON	4-PM	80			
HRS. WASHED		18 1/2			
M MHOS		249			
HRS. WASHED					
M MHOS					
HRS. WASHED					
M MHOS					
CAKE CONDITION					
NO CARS LOADED					
EXPLAIN LOSSES	278				

SAMPLES JAR
DELIVER TO

SAMPLED BY 270
RELEASED BY [signature]

== DRYING ==

DRY 12 HOURS AT 220 F.
THEN DRY 12 HOURS AT 200 F.
COOL TO 130 F.-----

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 15
LUMP WGT 2578

= GRINDING =

MILL 2 HSP 1/8"RP SCREEN 3700 RPM
MAX. TEMP. 140 F.
INERT MILL WITH CO2 WHEN GRINDING
PER D.F. 00.F. 0043.

SCREEN	RPM
MAX. TEMP.	F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 2 ENV
DELIVER TO CTL

DATE MIXED

RECEIVED BY
RELEASED BY

39
51
294

0.00 *

1.93 +
0.12 -
1.93 +
0.12 -
1.87 +
0.12 -
0.61 +
0.12 -
5.91 *

5.91 +
2.13 +
0.14 -
2.05 +
0.14 -
2.01 +
0.14 -
2.01 +
0.14 -
2.03 +
0.14 -
2.14 +
0.14 -
2.02 +
0.14 -
2.03 +
0.14 -
2.03 +
0.14 -
2.04 +
0.14 -
0.82 +
0.14 -
25.73 *