CG.01 CODE YE-698-D PKG ----

LOT MAY -0-81-E1028

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS = PRESSING =

VAT			
DATE			
TIME			
RELEASED BY			
PRESS	2	92	93
NO.OF CAKES	54	54	54

PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

SAMPLES
DELIVER TO

PRESSLOAD RECORD	1ST	2ND	3RD	4TH	5TH
STARTED					
CAKES USED					
WATER ON					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	7				

EXPLAIN LOSSES

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 18
NO CARS PULLED LUMP WGT 5732
SAMPLED BY
RELEASED BY

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR HIGH AIR FLOW

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY
RELEASED BY

1428
41
100

3.46	+
0.12	-
3.08	+
0.12	-
3.73	+
0.12	-
3.54	+
0.12	-
3.71	+
0.12	-
3.60	+
0.12	-
3.50	+
0.12	-
3.29	+
0.12	-
3.56	+
0.12	-
3.40	+
0.12	-
3.06	+
0.12	-
3.35	+
0.12	-
3.42	+
0.12	-
2.90	+
0.12	-
3.40	+
0.12	-
3.41	+
0.12	-
3.29	+
0.12	-
1.78	+
0.12	-
57.32	*

DUP050095836