

PLAINTIFF'S EXHIBIT

BIR-331

November 18, 1969

Mr. Art Plummer
Bird & Son
E. Walpole, Mass.

Dear Mr. Plummer:

Enclosed is Typical Test Data on our product
#456 Nicosat, glass strand reinforced asbestos
roofing felt.

If you can advise us a few days in advance of trial
with this product either George Adomshick or I will
try to be present.

Thank you.

Sincerely,

NICOLET INDUSTRIES, INC.


David P. Cortright
Marketing Manager

DPC/frr

cc: Mr. C. Holman, Bird & Son

Mr. G. Adomshick

BIRD 011205



NICOLET

INDUSTRIES, INC.

PRODUCT INFORMATION

WISSAHICKON AVE., AMBLER, PA. 19002

Phone: 215-646-4000

456 G NICOSAT (J.W. Type 450)

DESCRIPTION:

Norristown Manufacture

10# Asbestos Roofing Felt with
1/4" Spaced Parallel Strand
Glass Reinforced

PHYSICAL PROPERTIES:

	<u>Nominal</u>	<u>Max.</u>	<u>Min.</u>
Caliper	.0225	.024	.020
Basis Weight, #/100 ft ²	9.5	10.0	9.0
MD Tensile, #/in	27.0		20.0
CD Tensile, #/in	9.0		6.0
MD Tear, grams	11.0		7.0
Mullen	17.0		15.0
K. V. (burette)	55.0		52.0
Densometer	100	120	
% Asbestos	89.0		83.0

DATE November 12, 1968

PAGE 1 of 1

The enclosed represents typical laboratory data and Nicolet Industries, Inc. makes no representations or warranties in respect of the accuracy of information contained herein and shall incur no liability on account of the use thereof and does not hereby suggest, recommend, consent to, or induce the use of any process or the manufacture, use or sale of any product in violation of existing patents owned by Nicolet Industries, Inc. or others.