

LOT

MAY -0-81-E1501

ALTERNATE
TYPED BY JMH

EST'D WGT 3371

MAKING NOTES

TOTAL EST'D WGT= LBS (CRT ENTRY)

JOB NAME: 01YE698DPR

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 91 92 93
NO. OF CAKES 32 42 32 32
PRESS WITH AGITATION
WASH TO 2000 OHMS 35-74 F WATER
TEST AFTER 2 HOURS
LOAD ON 4 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 3353

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST GATE AT "9" FOR HIGH
AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1501
41
231

0.00 *

3.03	+
0.14	-
3.14	+
0.14	-
3.11	+
0.14	-
3.33	+
0.14	-
3.34	+
0.14	-
3.32	+
0.14	-
3.25	+
0.14	-
3.42	+
0.14	-
3.32	+
0.14	-
3.31	+
0.14	-
2.50	+
0.14	-
33.53	*