MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-787 LOT 38293

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1756	1	T-327		
1660	1	T-280		
	STUMP	LUMP 3445		

TOTAL NET WT. 3416 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

SK 12/23/80

N34735

22
244

CG 03 CODE KY-787-D PKG. ____

→DEC·17 80 38293

EST. WGT. ~~1090~~ LBS.

OK
H

3332

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (Q)	EWK 9/22/76
	DCG 9/27/76
RETYPED BY	
CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

VAT	244				
DATE	12-19-80				
TIME	10:15 AM				
RELEASED BY	A.C.				
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	

PRESS WITH AGITATION

WASH TO 2000 OHMS WITH 35-75 F WATER

TEST AFTER 2 HOURS

LOAD ON 6 CARS

SAMPLES 1-8 OZ JAR

DELIVER TO CTL FOR COLOR

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	12 Noo				
CAKES USED	46				
WATER ON	10 PM				
HRS. WASHED	4				
OHMS	3000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appeared dry
Released 12/22/80

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 15

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT. 3445

SAMPLED BY

RELEASED BY [illegible]

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 ENV & 1 PT. CAN

DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050105127

38293
41
188

0.00	*
2.49	+
0.12	-
2.53	+
0.12	-
2.60	+
0.14	-
2.45	+
0.12	-
2.52	+
0.12	-
2.49	+
0.12	-
2.46	+
0.12	-
2.42	+
0.12	-
2.42	+
0.12	-
2.57	+
0.12	-
2.57	+
0.12	-
2.58	+
0.12	-
2.20	+
0.12	-
2.17	+
0.12	-
1.80	+
0.12	-
34.45	*

6 cars.

15 decims

DUP050105128