

MD-3-A

## PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

R+539-D

LOT

38123

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PO

4

470

24

STUMP

LUMP 476

TOTAL NET WT.

470

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

WK

12 11 6 11 11

389

1 55+  
1 23+  
1 59+  
0 33+  
4 707

→ DEC -5 00 38123  
EST. WGT. 486 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES  
RT-539-D (N)

APPROVED BY  
EWK 10-25-77  
DCG 10-25-77

TYPED BY  
jlc 11-15-77

## MAKING NOTES

REMARKS

NAME: NAPHTHANIL® RED DARK

**BLEEDING**

## INSTRUCTIONS

**-PRESSING-**

## RECORD

|              |             |                         |  |                 |      |     |     |     |     |
|--------------|-------------|-------------------------|--|-----------------|------|-----|-----|-----|-----|
| VAT          | 260         |                         |  | PRESSLOAD       | 1ST  | 2ND | 3RD | 4TH | 5TH |
| DATE         | 12-5-80     | (5M)                    |  | STARTED         | 7:30 |     |     |     |     |
| TIME         | 3:10 AM     |                         |  | CAKES USED      | 36   |     |     |     |     |
| RELEASED BY  | [Signature] |                         |  | WATER ON        | 1:14 |     |     |     |     |
| PRESS        | 12          |                         |  | HRS. WASHED     | 8    |     |     |     |     |
| NO. OF CAKES | 36          |                         |  | OHMS            | 4000 |     |     |     |     |
| PRESS        | WITHOUT     | AGITATION               |  | HRS. WASHED     |      |     |     |     |     |
| WASH TO      | 4000        | OHMS WITH 35-75°F WATER |  | OHMS            |      |     |     |     |     |
| TEST AFTER   | 4           | HOURS                   |  | HRS. WASHED     |      |     |     |     |     |
| LOAD         | ON 3 CARS   |                         |  | OHMS            |      |     |     |     |     |
|              |             |                         |  | CAKE CONDITION  |      |     |     |     |     |
|              |             |                         |  | NO. CARS LOADED |      |     |     |     |     |
|              |             |                         |  | EXPLAIN LOSSES  |      |     |     |     |     |

**SAMPLES  
DELIVER TO**

SAMPLED BY

RELEASED BY

**- DRYING -**

DRY 20 HRS AT 180°F. LUMP: - OK - WET - SALTS - CONTAMINATED

**ADDITIONAL DRYING HOURS REQUIRED**

**SAMPLES  
DELIVER TO**

|                 |
|-----------------|
| NO. CARS PULLED |
| SAMPLED BY      |

NO. DRUMS: 4  
LUMP WGT. 476  
RELEASED BY P

**-GRINDING-**

MILL #5 LSP 1/8" RP      SCREEN 1750 RPM  
MAX. TEMP.      170 °F

|            |     |
|------------|-----|
| SCREEN     | RPM |
| MAX. TEMP. | OF  |

## EXPLAIN LOSSES

SAMPLE A L R WITHOUT MIXING  
SAMPLES. 1 Env  
DELIVER TO CTL

DATE MIXED

**SAMPLED BY**

RELEASED BY

0.00 \*

38123

58

85

0.00 \*

149.00 +

14.00 -

172.00 +

14.00 -

142.00 +

14.00 -

69.00 +

14.00 -

476.00 \*