

PRODUCT NAME = MOLYBDATE ORANGE

FORM 1 CODE YE-698-D PKG

LOT MAY -0-81-E1450

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

NON-BLEEDING

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 (92) 98
NO. OF CAKES 54 54 54
PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

1ST	2ND	3RD	4TH	5TH
11/30/81				
3				
4 AM				
5				
4000				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 19
LUMP WGT 5630

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

698
1450
41
56

0.00 *

15
3.17 +
0.12 -
2.98 +
0.12 -
3.26 +
0.12 -
0.12 -
3.36 +
3.39 +
0.12 -
3.27 +
0.12 -
3.26 +
0.12 -
3.30 +
0.12 -
3.46 +
0.12 -
3.24 +
0.12 -
3.43 +
0.12 -
3.42 +
0.12 -
3.23 +
0.12 -
3.27 +
0.12 -
1.31 +
0.12 -
45.55 *

1450
41
305

0.00 *

4
3.14 +
0.14 -
3.36 +
0.14 -
3.23 +
0.14 -
1.56 +
0.14 -
10.73 *
4555
5630