MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-788D LOT 36056

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	1	1758	T-65	
	1	1726	T-114	
	STUMP	3654		

TOTAL NET WT. 3,4184 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
RH	6/27/80	

N32217

22
Y240

CG 03 CODE KY-788-D PKG. ____

→ 24 36256

EST. WGT. 960 LBS.

Pump in 240 VAT

OK
AP

Total Wgt. 3560# Req(_____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/7
	DCG 9/27/7
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS -PRESSING- RECORD

AT	243				
DATE	6-21-80	(RM)			
TIME	2150				
RELEASED BY	SV				
PRESS	22	23	24		
NO. OF CAKES	46	46	46		

PRESS With AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5T
STARTED	8:45 PM				
CAKES USED	246				
WATER ON	1 AM				
HRS. WASHED	7				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	7				

EXPLAIN LOSSES

BLL

SAMPLES 1- 8oz JAR

DELIVER TO CTL for Color

SAMPLED BY #469 RELEASED BY AK

-DRYING-

Dry 12 hrs at 220 °F

Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINA

ADDITIONAL DRYING HOURS REQUIRED

No Drums 15

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3564

SAMPLED BY RELEASED BY BLL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 Env. & 1 Pt can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

N32217.01

DUP050457122



N32217.02

DUP050457123