



Occidental Chemical Corporation

RELATIVE VISCOSITY(1) / K VALUE(2) / POLYMERIZATION DEGREE(3)

RELATIVE VISCOSITY	K VALUE	POLYMERIZATION DEGREE
1.50	46	310
1.60	49	420
1.70	52	520
1.80	55	600
1.90	58	690
2.00	61	800
2.10	63	900
2.20	66	1005
2.30	68	1110
2.40	70	1220
2.50	72	1360
2.60	74	1490
2.70	76	1640
2.80	78	1780
2.90	80	1940
3.00	81	2100
3.10	82	2250
3.20	84	2400
3.30	85	2550
3.40	86	2780
3.50	88	3010
3.60	89	3220
3.70	90	3440
3.80	91	3650
3.90	92	3940
4.00	93	4150

(1) 1% by weight in cyclohexanone @ 25 C (OXY Test Method No. 500)

(2) 0.5 g/100 cc in cyclohexanone @ 25 C (DIN 53726)

(3) 0.2 g/50 ml nitrobenzene soln @ 30 C (JIS K 6721)

May 1989

NON WARRANTY: Occidental's recommendations or instructions as to handling, use, or disposal of any product, including its use alone or in combination with other products, or as to any apparatus or process, or the use of any products in connection therewith, are based upon information believed to be reliable, but Occidental makes no warranty and shall have no liability with respect thereto. Occidental's recommendations or instructions are not intended to suggest operations which would infringe any patents, and Occidental assumes no liability or responsibility for any such infringement.

OxyChem

PVC Resins and Compounds/PVC Fabricated Products Divisions

Armand Hammer Boulevard, Box 699, Pottstown, Pennsylvania 19464 215/327-6400

CHARDO 02079