

ONE

O'  BRIEN

Liquid-Lite
SATIN ENAMEL

HEAVEN BLUE

MADE BY THE O'BRIEN CORPORATION

SOUTH BEND, IND. • BALTIMORE, MD. • OKLAHOMA CITY, OKLA. • SAN FRANCISCO, CAL. • LOS

REGISTERED

LIQUID-LITE

REGN. No. 35(34)

Satin Enamel

DATE 3-4-64

DIRECTIONS FOR USE

New Wood — one coat of Double-Up Undercoat or White Surfacer. Follow with one or two coats of Liquid-Lite.

New Plaster — one coat of Liquid Velvet Wall Primer and Sealer. Finish with one or two coats of Liquid-Lite.

New Dri-Wall or Composition Board — one coat of O'Brien Vite. Follow with one or two coats of Liquid-Lite.

Unpainted Metal — same as listed under "New Wood".

Painted Surfaces in Good Condition — one coat of Liquid-Lite (providing there is no radical change in color).

Painted Surfaces in Poor Condition — one or two coats of Liquid-Lite.

Surface Preparation — sand surfaces well before painting. Remove dust, loose dirt, wax, polish, etc.

Application — use a soft bristle brush, short nap Mohair roller or spray gun.

Drying — dries to touch in 3 to 4 hours. Allow overnight drying between coats.

Thinning — use material as it comes from can. When thinning is necessary, use low odor thinners, turpentine, mineral spirits.

Tinting — light tints can be obtained with O'Brien Tone-All Colors.

LIQUID-LITE Satin Enamel

This top quality enamel is recommended for interior use on woodwork, cabinets, trim, walls, etc., whenever a rich, satiny finish is desired. Extremely popular for kitchens and bathrooms. Excellent for commercial and institutional work. May be used outdoors on porch and yard furniture.

IMPORTANT — USE OF DEEP COLORS

NEW WOOD OR METAL — one coat Double-Up or White Surfacer, followed by one or two coats Liquid-Lite Satin.

NEW SEASONED PLASTER — one coat of Liquid Velvet Wall Primer & Sealer (tinted with Deep Color), followed by one or two coats of Liquid-Lite Satin. (Over dry wall, plaster board or fresh plaster, use New Vite, tinted with Tone-All colors.)

PREVIOUSLY PAINTED SURFACE — one or two coats of Liquid-Lite Satin.

DRYING — allow at least 24 hours drying at not less than 68° F. between coats.

LEAD FREE
DO NOT TAKE INTERNALLY

DANGER!

HARMFUL OR FATAL IF
SWALLOWED

Do not induce vomiting. Flammable! Keep away from heat, sparks and open flame. USE WITH ADEQUATE VENTILATION. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after use. KEEP OUT OF THE REACH OF CHILDREN.

LIQUID-LITE SATIN ENAMEL	
Pigment	27.20%
Triphenyl Phosphate	18.40%
Triphenyl Carbamate	17.10%
Pigment	24.30%
Calcium Carbonate	100.00%
Vehicle	57.42%
Thinned Alkyd Resin	27.42%
Neat Treated Linseed Oil	3.00%
Neat Treated Pine Oil	1.00%
Mineral Spirits & Solvents	42.75%
	100.00%
Loss about 5% Thinning Colors advised	