#1
MEMBRANE

CG 46 CODE YC-11-A PKG. ____

→ DEC -5 80 38220

EST. WGT. 2238 LBS.

86"
TEMP AT START
186°F

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(D) YC-11-A	EWK 9-28-76
	BBK 10-17-77
	DCG 11-29-77
TYPED BY	
JTC 12-8-77	

MAKING NOTES

REMARKS

NAME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS						-PRESSING-	RECORD				
VAT	105					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	12-8-80					STARTED	6:45 PM				
TIME	6:35 PM					CAKES USED	62				
RELEASED BY	244					WATER ON	9:15 PM				
PRESS	32	33	35	M1		HRS. WASHED	6½				
NO. OF CAKES	60	62	60			OHMS	4000				

PRESS WITHOUT AGITATION
WASH TO 4000 OHMS WITH 35-75°F WATER
TEST AFTER 4 HOURS
LOAD IN METAL DRUMS AT 325# NET PER DRUM

A & L PRINTERS, NEWARK, N.J.
9 Blde
1/4 Scale

AIR BLOW PRESSCAKE 15 MIN AT 40PSI

NO. CARS LOADED

EXPLAIN LOSSES

Record: VAT TEMP

BJH

SAMPLES THIEF SAMPLE & FILL 1-8 oz. jar (1 qt PC-RdD)

DELIVER TO CTL for color

SAMPLED BY RELEASED BY

-DRYING-

DRY — HOURS AT — °F

DO NOT DRY

LUMP: — OK — WET — SALTS — CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES

NO. CARS PULLED

LUMP WGT.

DELIVER TO

SAMPLED BY

RELEASED BY

-GRINDING-

MILL SCREEN RPM

MAX. TEMP. °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

DATE MIXED

SAMPLES

DELIVER TO CTL

SAMPLED BY

RELEASED BY

N39411

WR
3647

N-15
128
N-120 -2 dwn
N-64

DUP050045818