MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky. 787 LOT 35132

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1750	1	T. 150		
1720	1	T. 135		
	temp STUMP	3531		

TOTAL NET WT. 3470 PKG. N--CODE

PROD. SPVR.	DATE	WHSE. OPER.

N32145

8-3
8-13

CG 03 CODE KY-787-D PKG. ____

→ [illegible] 36132

EST. WGT. 1090 LBS.

OK
AP

3490

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-787-D (Q)	EWK 9/22/76
		DCG 9/27/76
	RETYPED BY	
	CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM — NON-BLEEDING

INSTRUCTIONS — **-PRESSING-** — **RECORD**

VAT	253			
DATE	6-17-80			
TIME	2100 AM			
RELEASED BY				
PRESS	22	23	24	25
NO. OF CAKES	46	46	52	48

PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 6 CARS

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	8:30 AM				
CAKES USED	46				
WATER ON	1:30 PM				
HRS. WASHED	5				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				

EXPLAIN LOSSES

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY RELEASED BY

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 4

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 353

SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT. CAN
DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

N32145.01

DUP050456813

36132
4100
17

0.00	*
2.66	+
0.12	+
2.62	+
0.12	+
2.68	+
0.12	+
2.80	+
0.12	+
2.83	+
0.12	+
2.91	+
0.12	+
2.80	+
0.12	+
2.69	+
0.12	+
2.78	+
0.12	+
2.84	+
0.12	+
2.75	+
0.12	+
2.71	+
0.12	+
2.37	+
0.12	+
1.65	+
0.12	+
35.31	*

N32145.02

DUP050456814