REPRODUCED AT THE NATIONAL ARCHIVES

FORMULAE OF SPECIFIED PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MANUFACTURER 'C'

Outside White House Paint

Percentage Formula			Percentage Formula		
December 1940 to October 1941			November 1941 to June 1942		
	Percent			Percent	
Pigment		71.6	Pigment		71.2
Lithopone	31.2		H. O. Lithopone	31.1	
35% Leaded Zinc	29		35% Leaded Zinc	28.9	
White Lead	26.8		White Lead	23.5	
Magnesium Silicate	11.6		Magnesium Silicate	15.1	
Titanium Dioxide	1.4		Titanium Dioxide	1.4	
	100.0			100.0	
Vehicle		28.4	Vehicle		28.2
Alkali Refined Linseed Oil	82		Alkali Refined Linseed Oil	77	
Thinners and Driers	18		W.H.B. Oil	6.93	
	100		Thinners & Driers	16.07	
				100.00	
		100.0			100.0

Inside Flat White Paint

Percentage Formula

November 1940 to June 1942

	Percent	
Pigment		59.3
Titanium Calcium Pigment	90.50	
Silica	9.05	
Suspending Agent	.45	
	100.00	
Vehicle		40.7
Varnish and Oil	57	
Thinners and Driers	43	
	100	
		100.0

OPA 11065