

VISCOSITY WORK SHEET

Item 1277-1281 P.T.No. _____ Date 11/31/56
 Worker Stanley Polymer Lucite Solvent CHCl₃
 For Biogel Charge 13.59 Temperature 20°C
 Viscometer No. III Efflux Time 152.2/152.1 Weight: Gross 3.6073
 Viscometer No. 8 Efflux Time 159.7/159.8 Tare 3.4893
 Viscometer No. A Efflux Time 170.1/170.1 Net 0.1250

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh. Visc. or M.W.
5028-151-1	4C	III	189.3; 187.5; 187.2	1.232	0.42
"	E0	8	197.9; 197.7; 197.8	1.238	0.43
5028-39	00	A	207.4; 207.2; 207.5	1.217	0.39
"	DZ	III	183.7; 184.0; 183.8	1.210	0.38
5028-149A	GA	8	206.8; 207.4; 207.0	1.296	0.52
"	ZE	A	218.6; 218.6	1.286	0.50
5028-150	ZY	III	187.0; 187.0	1.230	0.41
"	H5	8	197.1; 197.2; 197.1	1.233	0.42
5028-151-2	X	A	204.2; 204.1; 204.3	1.201	0.37
"	0-1	II	181.4; 181.6; 181.7	1.193	0.35

PC-1

N38886

2-1-56
may