MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky-787 LOT 37689

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2080	1	T-193		
1700	1	T-158		
1700	1	T-22		
	STUMP	STUMP	5392	

TOTAL NET WT. 5480 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

11,7,80

N34716

95/162

DCG 03 CODE KY-787-D PKG. ____

→ NOV -3 80 37689

EST. WGT. ~~1921~~ LBS.

TOTAL WGT 5845# (REQ ____)

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-787-D (S)	EWK 10-19-77
	Alternate	DCG 10-25-77
	TYPED BY	
	JIC 11-4-77	

MAKING NOTES

REMARKS

NAME: KROLOR® YELLOW-MEDIUM NON-BLEEDING

INSTRUCTIONS				RECORD					
VAT			262	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			11-5-80	STARTED	1 PM				
TIME			10:45A	CAKES USED	72				
RELEASED BY			[illegible]	WATER ON	6 PM				
PRESS	98	96	95	HRS. WASHED	4				
NO. OF CAKES	70	72	72	OHMS	10,000				
PRESS WITH		AGITATION		HRS. WASHED					
WASH TO	2000	OHMS WITH 35-75°F WATER		OHMS					
TEST AFTER	4	HOURS		HRS. WASHED					
LOAD ON 10 CARS				OHMS					
				CAKE CONDITION					
				NO. CARS LOADED	10+3				
				EXPLAIN LOSSES	Pressure gage on fill line blew off while pressing — unknown amount of color lost				
SAMPLES 1-8 oz. JAR				SAMPLED BY		RELEASED BY			
DELIVER TO CTL FOR COLOR									

-DRYING-

DRY 12 HRS AT 220°F.
THEN DRY 8 HRS AT 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

Pressure gauge on fill line blew off
Reason for color loss
Released Batch

ADDITIONAL DRYING HOURS REQUIRED

No. Drums: 32

SAMPLES
DELIVER TO

NO. CARS PULLED 13 LUMP WGT. 5392
SAMPLED BY RELEASED BY CC

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 env + 1 Pt Can
DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050105043



DUP050105044

DUP050105045