

EST. WGT.

3371

LBS.

(E) YC-10-B

DCG 11-18-76

TYPED BY

jlc 11-24-76

MAKING NOTES

REMARKS

ME MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT	241					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	4/16/81					STARTED	10PM				
ME	9:40PM					CAKES USED	34				
RELEASED BY	PAI					WATER ON	13PM				
RESS	2	91	92	93		HRS. WASHED	2				
J. OF CAKES	32	42	32	32		OHMS	2500				
RESS	With	AGITATION				HRS. WASHED					
ASH TO	2000	OHMS	with 35-75°F water			OHMS					
EST AFTER	2	HOURS				HRS. WASHED					
OAD on 4 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	4				
						EXPLAIN LOSSES					
MPLES											
ELIVER TO						SAMPLED BY					
						RELEASED BY					

-DRYING-

EXTRUDED) DRY 12 HOURS AT 240°F	LUMP: - OK - WET - SALTS - CONTAMINATE
NOT EXTRUDED) DRY 14 HOURS AT 240°F	
	ADDITIONAL DRYING HOURS REQUIRED
MPLES 1 ENV	NO. CARS PULLED
ELIVER TO CTL	SAMPLED BY
	RELEASED BY
	NO. Drums
	LUMP WGT. 3384

-GRINDING-

ILL Mikroatomize	SCREEN	RPM	SCREEN	RPM
MAX. TEMP.	°F		MAX. TEMP.	°F
SET ROOF BLAST GATE AT "9" FOR			EXPLAIN LOSSES	
HIGH AIR FLOW				
SAMPLE A-13 / WITHOUT MIXING			DATE MIXED	
MPLES 1 Env				
ELIVER TO CTL			SAMPLED BY	
			RELEASED BY	

1043
41
231

0.00 *

3.54 +
0.12 -
3.45 +
0.12 -
3.71 +
0.12 -
3.36 +
0.12 -
3.55 +
0.12 -
3.40 +
0.12 -
3.31 +
0.12 -
3.76 +
0.12 -
27.12 *

1043
41
56

0.00 *

27.12 +
3.41 +
0.12 -
30.41 *

1043
4100
18

0.00 *

30.41 +
3.57 +
0.14 -
33.84 *