

VISCOSITY WORK SHEET

Item 993-994 P.T.No. _____ Date 1/23/56
 Worker Stanley Polymer Lucite Solvent C2Cl3
 For Comparison Charge 1329 Temperature 20°C
 Viscometer No. III Efflux Time 152.1; 152.1 Weight: Gross 3.6078
 Viscometer No. 8 Efflux Time 169.7; 169.8 Tare 3.4828
 Viscometer No. A Efflux Time 170.2; 170.1 Net 0.1250g/0.5ml

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh. Visc. or M.W.
5146-33C	H-6	III	193.6; 193.6	1.273	0.48 ✓
"	VI	8	203.6; 203.7; 203.9	1.275	0.49 ✓
5146-33D	BB	A	217.0; 217.1; 217.0	1.276	0.49 ✓
"	J-5	III	193.4; 193.4	1.273	0.48 ✓

PC-1

May
1-26-56

ch
JRK