MD-3-A

PACKAGE TICKET

CODE Ky-908 LOT F2H73

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
	2080	1	T-40	
	2080	1	T-102	
	874	1	T-299	
SB	50	25	1250	
	STUMP			

TOTAL NET WT. 6284

LUMP WT. 6115 PKG. N-CODE

PROD. SUPV. [illegible] DATE 6-11-82 OPERATOR

N38014

PRODUCT NAME = KROLOR YELLOW-LIGHT — NON-BLEEDING — 1/28/82

CG 03 CODE KY-908-D PKG ____ — PROCESSES KY-908-D (F) — APPROVED BY FWP 12/10/81

95 / 240

LOT MAY 28 1982 F2H73

TYPED BY JMH

MAKING NOTES _____

EST. WT. 6110* LBS.

JOB NAME: 03KY908DPF

INSTRUCTIONS = PRESSING =					RECORD					
VAT		240			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		6-7			STARTED	730AM				
TIME		5PM			CAKES USED	72				
RELEASED BY					WATER ON	11PM				
PRESS	96	96			HRS. WASHED	5				
NO. OF CAKES	72	72			M MHOS	178				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 500 M MHOS - 135-145 F WATER					M MHOS					
TEST AFTER 3 HOURS					HRS. WASHED					
LOAD ON 10 CARS					M MHOS					
					CAKE CONDITION					
					NO CARS LOADED	44				
					EXPLAIN LOSSES					

SAMPLES DELIVER TO

SAMPLED BY
RELEASED BY FWP

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 21
LUMP WGT 6115

SAMPLES DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY FWP

= GRINDING =

MILL 939 HSP 3/32"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY 814 / 1250 / 1124

DUP050046529

73
41
348
0
310
12'
315
12'
314
12'
315
12'
322
12'
325
12'
324
12'
323
12'
317
12'
316
12'
306
12'
12
317
12'
315
12'
312
12'
326
12'
322
12'
325
12'
305
12'
315
12'
293
12'
62
12'
6115
0

10 cars

21 [illegible]