

FORMULA RECORD

Exp. No. _____ Date 7-1-35 Rez. No. 71

Name Porch & Deck - Dark Brown Card No. 1 See No. _____

182	LBS.	132	Customer	<u>S. W. Co.</u>
46	"	12310	To Match	<u>Std. - Color Chip</u>
11	"	54	Weight Per Gal.	<u>10.48</u> Visc. <u>23"</u> #3 @ <u>75° F.</u>
4 1/2	"	104	Baume.	<u>Std. of Fineness 2 P</u> ☐ Red ☒ No Label Required
60	"	20 L 9-12-35	Base	<u>Lbs. Gals. per hour</u> <u>Mill</u>
92	"	1526 577#	New Std. Sample Required	<u>Yes</u> Date Rec'd _____
6	GLS (2)		Reason for Revision	<u>Rx Assignment</u>
4	GALS. (504)		<i>See Card #2</i>	
10	" (1741)			
4	" (348)			
42	" (2960 A)			
20	" (2281)			
5	" (392) (21)		Normal Output	<u>100</u> Approved Formulator _____
1	" (1767)		Est. Mfg. Loss	<u>3%</u>
1/4	" (12 W)		Department	<u>B</u> Supt. <u>J. D. ...</u>
1/2 X	" (152)	X	Label Analysis Checked - Date	_____

A135 4-35 3321 B

MANUFACTURING INSTRUCTIONS:

Reduction: Amount _____ Reducer Used _____

Application: Surface Wood-Metal-Canvas Method Brush

No. Coats One Undercoater Used _____

Drying Time: Touch _____ Handle 6-8 Hrs. Recoat O'night

Rub _____ Sand _____ Wrap _____ Stencil _____

Baking Time and Temp. _____

Gloss Enamel Film Tough & Hard

Special Tests Matched to F. O. Pierce color card Seal Brown

FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND	<u>7-1-35</u>			ALLIED RESEARCH	<u>7-22-35</u>		
NEWARK	<u>6-27-35</u>	<u>6-27-35</u>		GIBBSBORO			
KENSINGTON	<u>7-22-35</u>	<u>7-22-35</u>		DAYTON			
OAKLAND				DETROIT			
DALLAS				LONDON			
LOS ANGELES				AUSTRALIA			
MONTREAL	<u>7-1-35</u>						
COSTA MESA	<u>7-1-35</u>						