



INTERNAL CORRESPONDENCE

FILE COPY

PLAINTIFF'S EXHIBIT

UC-3045

CHEMICALS AND PLASTICS

P. O. BOX 8361, SOUTH CHARLESTON, WEST VIRGINIA 25303

To (Name) Mr. J. J. Dlugos, Jr.
Division Building 2000-303
Location Technical Center
Copy to MOC

Date October 31, 1968
Originating Dept. Research and Development
Subject Johns-Manville-61
Asbestos Gasket Material

Dear Mr. Dlugos:

You recently submitted a piece of Johns-Manville No. 61 asbestos gasketing material for evaluation and comparison with our other standard asbestos gasket products.

Analysis shows the JM-61 to contain 22% of a synthetic elastomer best defined as a Buna-S. This is comparable to the binder used in Garlock 7735 or U.S. 899. Burning the material did not reveal any appreciable sulfur contained in the material. The hardness of the product was Durometer A-67 as compared with 68 for the 899 and 7735.

We would consider the JM-61 to be comparable to Garlock 7735, U.S. 899, or Raybestos-Manhattan 2700. You recall that some years ago we dropped the Garlock 7021 from our list of approved gasket materials because of the natural vulcanized rubber used as the binder in the sheeting. This contained sulfur which was undesirable in certain meticulous polymerization exposures, and in general, the product did not have quite the chemical resistance of the 7735.

If there is additional information regarding this material that you wish to obtain, we will be happy to pursue the subject further.

Very truly yours,

L. S. VanDelinder

LSV/bh

9526 Index: 23, 50, 112, 180,
306, 308

UCC 001883