

GENERAL

Revised 8/56 to O-131

The Montanans are a series of high-melting, dark-colored products of somewhat variable composition of which the following are representative:

TYPICAL PROPERTIES OF THE MONTARS

Monter #3

Softening Point (ASTM)	130-160°C.
Flash Point	570°F. (298°C.)
Fire Point	None at 650°F. (343°C.)
Acidity (Mgm. NaOH/gm.)	Slightly basic
Chlorine	51.6 %
CaO	3.47%
Fe	0.31%

Montar #4

(Polychlorinated polyphenyl)	
Softening Point	191-208°C.
Penetration, 250 gm. weight	0 @ 75°C.

Montar #5

(Polychlorinated polyphenyl)	
Chlorine	57-59.0%
CaO	Max. 1.6%
Fe	Max. 0.12%
Softening Point	165-180°C.
Penetration, 250 gm. weight	2 cm. x 10 ⁻² /min. @ 75°C.

Montar #6

(Polychlorinated polyphenyl)	
Softening Point	168°C.
Chlorine	59.9 %
CaO	2.0 %
Fe	0.13%

Montar #9

Softening Point (ASTM)	140-160°C.
Flash Point	495°F. (257°C.)
Fire Point	580°F. (304°C.)
Acidity (Mgm. NaOH/gm.)	0.104
Chlorine	0.18%
CaO	None
Fe	0.21%

Montar #10

(Mixed Polyphenyl and polychlorinated polyphenyl)
Softening Point 139°C.
Penetration 47 cm. x $10^{-3}/5$ sec. @ 75°C.

*Reg. U.S. Pat. Off.

0222134

The information contained in this bulletin is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. The Monsanto Chemical Company disclaims any liability incurred in connection with the use of these data or suggestions.

Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

MONITOR

Monsanto Technical Bulletin

October 1, 1953

0114.22

TOWOLDMON0026755