MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE RT-695 LOT 34896


NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	10	1975	20	
	STUMP			

TOTAL NET WT. 1975 PKG. N--CODE

PROD. SP.VR. DATE WHSE. OPER.

3 22 80 483

DUP050292535



DUP050292536

N 31853.01

36/100 → 100

CG 36 CODE RT-695-D PKG. ____

MAR 15 34896

EST. WGT. 1350 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

36/100

PROCESSES	APPROVED BY
RT-695-D (M)	DCG 1-12
	THD 2-25
TYPED BY	
LG 5-15-72	

~~Retyped 2-27-80~~ MnM

MAKING NOTES

REMARKS

NAME: BON RED DARK

NON-BLEEDING

INSTRUCTIONS –PRESSING– RECORD

VAT	100				
DATE	3-16-80				
TIME	10 PM				
RELEASED BY					
PRESS	32	33	~~35~~ 36	38	39
NO. OF CAKES	60	60	30	60	60

PRESS Without AGITATION

WASH TO 4000 OHMS with 35-75F water

TEST AFTER 16 HOURS

LOAD on 8 cars

SAMPLES

DELIVER TO

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	5 PM				
CAKES USED	30				
WATER ON	12:30 PM				
HRS. WASHED	15				
OHMS	7000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	4				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY BLL

–DRYING–

HOURS Dry 24 hours at L.V. H.V.

TEMP. 180 °F °F

SE 15-30

Mn Color

LUMP: – OK – WET – SALTS – CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO. CARS PULLED 8

SAMPLED BY

LUMP WGT. 1370

RELEASED BY

–GRINDING–

MILL 5 HSP 1/8" RP SCREEN 4600 RPM

MAX. TEMP. °F

Mn Color

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

CO_2 USAGE: 2-2-9 %

OXYGEN 229 3/20/80

SAMPLE AFTER / WITHOUT MIXING

SAMPLES Env & 2 pt cans

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050292537

N 31853.02

3 4 8.9 6	#
.5 1	#
3.2 4	#
.0 0	T
1.8 6	
.1 4	-
2.0 7	
.1 4	-
2.0 1	
.1 4	-
2.0 8	
.1 7	-
1.9 3	
.1 4	-
2.0 1	
.1 4	-
1.9 0	
.1 7	-
1.0 5	
.1 7	-
1 3.7 0	T

DUP050292538

N 31853.03