

SUMMARY OF VCM MONITORING BY DISTRIBUTION DEPARTMENT

Report Date (Test Date)	Product Resin	Lot No.	Pkg.	AVCM ppm		RVCM ppm		\$ Reduced	Test Conditions, Etc.	Location & Comments
				Back	Front*	Initial	After 72 Hrs.			
11/14/74	G-92	L-22286	10	.018 .028	.019 .017	13.4	7.37	45	49°F. Unheated Trailers	ALDC
(11/11/74)		L-22290	10	---	.170	5.53	5.32	4	"	"
				.055	.170	3.37	4.19	-24	"	"
						4.41	3.28	26	"	"
						12.3	7.53	29	"	"
		L-22292	10	.170	.270	79.9	15.7	80	"	"
				---	.150	120	72.7	40	"	"
		MT Trailer		.065	.049					
11/18/74 (11/8/74)	103-EP	L-2106	10				144		49°F. Unheated Trailers	Louisville
		1 Skid			4					
		2 Skids			15					
		4 Skids			29					
		9 Skids			12 & 14					
		L-2107					119			
		1 Skid			6					
		2 Skids			26					
		4 Skids			35					
		9 Skids			16 & 29					
12/11/74 (11/19/74)	102-F5	Samples								
	Full Compartment	1 & 2	90	15.9, 10.1		27			48°F. Bulk Railcar	Acton, Mass. Bulk Term.
	MT Compartment	3 & 4		26.5, 21.9						
	Bottom Outlet	5 & 6		.26, .43						
11/18/74 (11/12/74)	121	L-950139	10	.05, .07					40°F. Open Warehouse Storage	Keimer Whse., Chicago
12/11/74 (11/18/74)	80X5	L-545209	10	.08, .33					48°F. Open Warehouse Storage	Sack Storage, Worcester, Mass.
12/11/74 (11/18/74)	80X5	L-545107	10	.11, .11 .05, .06					40°F.	Sack Storage Trailers from Fed. D.C.

* Back - Front refer to sample location in truck trailer.

RJS/pac
2/17/75

BFG27169

23770001

BFG27170

- 2 -

Report Date (Test Date)	Product	Lot No.	Pkg.	AVCM ppm		RVCM ppm		%	Test Conditions, Etc.	Location & Comments
				Back	Front *	Initial	After 72 Hrs.			
12/20/74 (12/10/74)	120X241 121 83421 83794	One Sample Point	10	.32, .32					60°F. Open Warehouse Storage	California Warehouse
12/20/74 (12/10/74)	124 131 120X241 82491 8883		10	.33, .46					60°F. Open Warehouse Storage	California Warehouse
12/20/74 (12/10/74)	222	L-02177	10	1.40, .99					Trailer w/2 skids of product left to be unloaded.	California Warehouse
1/24/75 (12/6/74)	103	L-28766 4 Skids 9 Skids	10	.37	.78	.49 .63 .55 .42	.88 1.21 No Test "		Unheated Trailer " " Sample Time - 6 Min. - 2.2 ppm Sample Time - 16 Min. - 2.0 ppm	ALDC Lou Wagner, Monitored
	MT Trailer G-92	L-22322 16 Skids	10	1.0 .63	.97 .82	.43 1.07 1.78 1.26 2.62 1.86	" 1.51 2.18 2.83 2.14 1.87			
1/10/75 (11/27 - 12/2/74)	135 2 Skids 9 Skids Full		10	Nil Nil	.5 .8 .5				Unheated Trailer 72 Hrs.	Louisville
(12/6-12/9/74)	121 9 Skids Full		10	.5	.6 Nil				10 Minute Sample Time - Driver Monitored, Nil	"
(12/12-12/16/74)	103-EP 4 Skids 9 Skids		10	1.8 No Data					10 Minute Sample Time - Driver Monitored .8 ppm " "	
1/3/75 (12/12/74)	121	L-00004	10	.109, .156					40°F. Raining	OK Trucking Terminal
		L-00007		.334					15 & 20 Minute Sample Time - .1 ppm.	Driver Monitored <.1 &

23779002

Report Date (Test Date)	Product	Lot No.	Pkg.	AVCM ppm		RVCM ppm		Reduced	Test Conditions, Etc.	Location & Comments
				Back	Front*	Initial	After 72 Hrs.			
12/3/74 (11/25/74)	121 130K24 128 121	L-22727	10 10	0.05 0.21					60°F. " Open Warehouse Storage	Carolina Transfer " "
2/13/75 (1/10/75)	121	L-22760 MT Trailer Trailer Before Opening Trailer After Opening	10	.5 1.2 1.0			.3		Heated Trailer (after 3 days at 100°F.)	ALDC
1/6/75 (12/13/75)	G-92 Bulk Truck		70	3.1 (5.5, 6.9)	.453				35°F Outside Transfer Area 15 & 20 Min. Sample Time - 55°F. Bulk Loading Area 102 Min. Sample Time - Driver - 102 Min. Sample Time - Bulk Loader - 118 Min. Sample Time - Inspector -	Marietta Plant. Truck driver monitored 4.1 & .2 ppm. (Sample taken at tanker/ outlet) Avon Lake plant - monitoring Bldg. 452 .29 ppm 1.0 ppm .55 ppm
12/6/74 (11/15/74)	Compound 8700A Green 535	L-25033 Skid 4 Skid 6 MT Trailer	10	--- .18 .14	.16 .2 .21	N11	N11		Unheated Trailers Bags	ALDC
	85414 Blk 288	L-25053	10	1.8 1.7	3.3 3.8	230 195	261 323		Bags	
	8700A Blk 293A	L-25136 Skid 2 Skid 4 Skid 5 Skid 10	10	2.9 5.4	12 10	142 N11 N11 N11	140 142 176 228		Bags	
1/10/75 (12/20 - 12/23/74)	8720 Blk Full Truck 83741 Gray		10	N11 1.4					Truck driver monitored 10 Min. Sample Time - 0.6 ppm (Louisville)	
12/20/74 (12/10/74)	83741 Nat 021 83794 Blk 288 8883 Trans 001 83994 Blk 288	L-73208 L-0064 L-73237 L-0064	10 10 10 10	1.01, 1.10 1.20, 1.40					60°F. Open Warehouse Storage	California Warehouse California Warehouse

BFG27171

23770003

BFG27172

- 4 -

Report Date (Test Date)	Product	Lot No.	Pkg.	AVCM ppm	RVCM ppm		Reduced	Test Conditions, Etc.	Location & Comments
					Initial	After 72 Hrs.			
1/3/75 (12/12/74)	83794 2 Skids	L-0156	10	.035,.082				40°F. Raining	OK Truck Terminal Cleveland, Ohio
12/11/74 (11/26/74)	84209 Blk 288 80644 Nat 021 8806-021 8818 Nat 021 84209 Blk 288 80534 Gray 243 8806 Nat 021 8801 Nat 021 80644 Nat 021 8806 Nat 021	L-540909 L-540804 L-00074 L-0041 L-540909 L-540731 L-00073 L-540910 L-540804	60 60 60	.081 0.87,0.87 0.60,0.71 0.40				50°F. Open Warehouse Storage	Consumers Warehouse CT-200 Boxes Samples taken over open CT-200's
12/11/74 (11/18/74)	H1-temp 88925 Green 514 LATKX		60	0.34				48°F. Open Warehouse Storage	Sack Storage CT-200 Boxes
12/11/74 (11/18/74)	Geon Latex 660X2 Geon 101-P4 Geon Latex 652 Geon Latex 450X167		30 30	0.24 1.07				Heated Room Heated Room	Sack Warehouse Fibre Drums Fibre Drums
11/18/74 (11/12/74)	Geon 576 Geon 354 Geon 354 Geon 580X12 Geon 576 HL. 05593		30 40 40 40	0.56,0.73 0.24,0.29 0.12,0.14 0.11,0.13				Basement Area Basement Area Basement Area Basement Area 60°F. Open Warehouse Storage	Kelmer Warehouse Fibre Drums Steel Drums Steel Drums Steel Drums
12/3/74 (11/25/74)	Geon 660X1 Geon 352 Geon 580X12 Geon 576 Geon 577 Geon 580X83 Geon 576 Geon 580X12		30 30 30 30 30	.06,0.78 2.60,2.30 6.10,4.70				65°F. Heated Room 65°F. Heated Room 65°F. Heated Room	Carolina Transfer Fibre Drums Carolina Transfer Fibre Drums Fibre Drums Carolina Transfer Fibre Drums
2/13/75	Geon 352 MT Trailer Trailer During Loading Trailer Before Opening During unloading & sampling	L-20314	30	.5 .6 4.0 .5,.6	275	275 after testing		Heated Trailer After 5 days at 95°F.	ALDC Fibre Drums

23770004