

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A. Stasenko AT Burl. Compound DATE September 22, 1969

FROM E. L. Kanyok AT Burlington COPY TO H. B. Carr

SUBJECT Firestone 250 Resin W. C. Champion

 H. H. Duhamel

 P. Gawason

 P. R. Scarito

 D. H. Weintraub

 File ✓

The results of Firestone 250 resin received on 9/19/69 are as follows:

<u>Properties</u>	<u>Truck #99</u>	<u>Truck #285</u>	<u>Burl. 250-12 Spec.</u>
Relative Viscosity	2.45	2.48	2.40 - 2.48
Gels	11	12	12 Maximum
Dry Blend	7.2	7.5	6.0 - 8.0
Screen			
+40	Tr	Tr	-
+60	Tr	Tr	0 - 3
+80	8	12	-
+100	58	58	50 - 80
+140	88	.87	-
+200	99	97	-
Thru	1	3	0 - 5

E. L. Kanyok
E. L. Kanyok

ELK/rjl