PYDRAUL®

Fire-Resistant Hydraulic Fluid

SELECTOR

A guide to selecting the correct Pydraul fluid for your hydraulic system.

O-FF/3

Monsanto

Correction pg. 6

0237403

TOWOLDMON0027615
WATER_PCB-00012084



Graph on Pg. 6 is incorrect.

A Sticker graph will be placed over it.

0237404

TOWOLDMON0027616
WATER_PCB-00012085

PYDRAUL®

Fire-Resistant Hydraulic Fluid

SELECTOR

A guide to selecting the correct Pydraul fluid for your hydraulic system.

O-FF/3

FUNCTIONAL FLUIDS Monsanto

Nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use. The information contained herein is, to our best knowledge accurate; but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. Monsanto disclaims any liability for loss or damage incurred in connection with the use of the above.

Registered Trademark of Monsanto Company

Organic Division / 800 N. Lindbergh Blvd. / St. Louis, Missouri 63166

0237405

TOWOLDMON0027617
WATER_PCB-00012086

PYDRAUL® FLUIDS

Development

Fire protection for industrial hydraulic operations began with Pydraul in 1951. Pydraul fluids have since served industry with millions of machine hours of fire-free operation. Pydraul fluid has never contributed to a fire — not even when sprayed from the broken ends of high pressure hydraulic lines onto white-hot surfaces.

New ways are continuously being explored to improve the excellent performance records of Pydraul fluids. The first Pydraul fluid, general-purpose Pydraul F-9, has grown to a family of six, specially tailored, fire-resistant hydraulic fluids. Each answers a major but specific hydraulic fluid need for industrial use. In addition to guarding against fire, each Pydraul fluid lubricates as well as premium grade oil. Pydraul fluids have answered the need of virtually every industrial hydraulic operation, indoors and out — from the sub-zero, outdoor hydraulic lift operations for refineries and blast furnaces to the low-viscosity fluid demands of high-speed, precision machine tools.

Performance

Pydraul fluids offer a wide range of viscosities from which you can select the proper range specified by your hydraulic equipment manufacturer. Whichever Pydraul fluid you select, each provides the same protection against fire, premium lubricity, ease of maintenance, and freedom from corrosive action and foam. Pydraul hydraulic fluids also offer several additional benefits —

REDUCED FIRE INSURANCE RATES

Pydraul eliminates fire hazards from hydraulic operations, reduces fire threats to surrounding structure and equipment. Insurance premiums for plants using Pydraul are often lower than premiums for operations using petroleum oil.

LONGER PUMP LIFE

Machines that operate on water-based fluids frequently require pump repair or replacement as often as every two or three months. Machines that use Pydraul hydraulic fluids can operate on the same pump for several years. Pydraul hydraulic fluids give the same long pump life as the finest grade petroleum oil.

NO CORROSION PROBLEMS

Any metal hydraulic system component in contact with Pydraul will not rust. Pydraul hydraulic fluids do not lose anti-rust properties even after extended use.

MAXIMUM EQUIPMENT RESPONSE

Pydraul never produces excessive froth or foam during normal operations to interfere with hydraulic equipment response. Because Pydraul hydraulic fluids lubricate as well as premium petroleum oils, Pydraul permits equipment to operate at optimum response capability.

INSPECTION AND REPLACEMENT DOWN-TIME ARE VIRTUALLY ELIMINATED

Pydraul hydraulic fluids are designed to be permanent. Pydraul fluids do not wear out. Except for normal "make-up" requirements, you never have to add new Pydraul to hydraulic systems. Pydraul eliminates "drain and change" periods; it does not have to be inspected in your system from month to month — or even replaced from year to year.

0237406

TOWOLDMON0027618
WATER_PCB-00012087

Converting to Pydraul is Easy

No matter what type of hydraulic fluid you now use in your equipment, you can easily convert to Pydraul. Virtually every type of hydraulic machinery requiring a fire-resistant hydraulic fluid has been converted to Pydraul. Equipment manufacturers are experienced in converting machinery to Pydraul and should be consulted for their specific recommendations. Some manufacturers will tell you exactly what seals to change. Most can supply the correct seals.

Machines operating on a *straight synthetic*, fire-resistant fluid can be converted to Pydraul without interrupting your production. When converting to Pydraul A-200, Pydraul 625, or Pydraul AC, simply add Pydraul as make-up. To convert to other Pydraul fluids, drain the old fluid and refill with the Pydraul fluid. No flush is necessary. For best seal performance, make your future seal selection according to recommendations in the booklet "Converting to Pydraul® Hydraulic Fluids."

Machines operating on oil or water-based hydraulic fluids require the few simple steps outlined below. These steps are necessary to clean the system of the old fluid and to change to dynamic seals compatible with Pydraul.

CHECK FOR LEAKS

Check your entire system for leaks before you shut down. Mark any leaks for sealing after the system is drained.

DRAIN THE SYSTEM

Drain your present fluid as completely as possible from reservoir, lines and cylinders. Flush system with steam or warm water to avoid residual oil and water-glycol sludge that can reduce Pydraul fluid fire-resistance. You may also be able to do this by opening unions at low spots in your system and blowing out with clean dry air. Seal any leaks.

CLEAN RESERVOIR AND FILTERS

If your reservoir is painted, use a commercial paint remover or scrape out the interior to prevent paint deterioration later on. Wipe your reservoir clean with lint-free rags. Clean or change the cartridge in your filter.

CHECK PUMPS

Check your pumps thoroughly for wear. Replace any worn parts.

CHANGE SEALS, PACKINGS AND HOSES

Change your dynamic seals to seals compatible with Pydraul hydraulic fluid. If you use reinforced type hoses that are in good condition, you normally won't need to change them. If your hoses undergo severe flexing, we recommend butyl or Teflon-lined hoses. Your accumulator diaphragms should be of butyl, fluoroelastomers, EPR or silicone. Avoid buna elastomers, neoprene and natural rubber.

RECONNECT LINES

Reconnect your lines, and tighten firmly. Fill your system with Pydraul to the manufacturer's recommended level.

START AND STOP PUMP

With the hydraulic controls in neutral, start and stop your pump several times, without allowing the system to reach working pressure. This procedure will lubricate the pump. Then you can leave the pump on to bring the system up to working pressure.

RUN THROUGH CYCLE

Run through the full operating cycle several times to use all parts of your system. Bleed any trapped air through the petcocks. Check your fluid level and add Pydraul if necessary.

ASK FOR THE BOOKLET

"Converting to Pydraul® Hydraulic Fluids," for complete information.

HOW TO EQUIP NEW MACHINERY WITH PYDRAUL

When ordering new hydraulic equipment, simply specify, "For use with Pydraul hydraulic fluid" and state the specific Pydraul you will use.

0237407

TOWOLDMON0027619
WATER_PCB-00012088

Pydraul® Selector	PYDRAUL F-9	PYDRAUL 60
PHYSICAL PROPERTIES Appearance	Cloudy Blue Liquid	Cloudy Blue Liquid
Spec. Gravity 25°/25°C	1.280—1.295	1.088—1.091
Neutralization No. (acidity) (mg KOH/gm) max.	0.12—0.35	0.25
Moisture (max.)	0.20%	0.10%
VISCOSITY As measured: 100° F. 210° F. "Absolute Saybolts" 100° F. (SSU X Density) 210° F.	 225 SSU 43.3 SSU 327 SSU 52 SSU	 60 SSU 35 SSU 60.5 SSU 35 SSU
Pour Point	−5° F.	−70° F.
Compressibility $X10^{-6}$ sq. in./lb.	2.58	3.05
Bulk Temperature Max.	300° F.	200° F.
Boiling Point °F at 760 mm Hg.	644° F.	707° F.
Cofficient of Thermal Expansion per °F.	0.00041	0.00044
Specific Heat (BTU/lb./° F.) (@ 77° F.)	0.32	0.42
Thermal Conductivity BTU/hr./ft./° F.	0.067	0.047
Vapor Pressure Hg @ 200° F.	0.1mm	0.01mm
Bulk Modulus (Room Temp. 1000-6000 psi)	387,000	328,000
Solubility in Water	Negligible	Negligible
FIRE RESISTANCE TEST		
High Pressure Spray Test AMS-3150B and MIL-F-7100. Test fluid sprayed at 1000 psi through orifice, passing through flame of oxyacetylene torch, 6000° F.	Does not flash or ignite up to 3½ feet from orifice.	Self-extinguishing
Low Pressure Spray Test (AMS-3150B). Test fluid sprayed at low pressure over ignited, oil-soaked rag to determine degree of increase in flame intensity.	No increase in flame intensity.	Slight increase in flame intensity.
Hot Manifold Test (MIL-F-7100). Test fluid dripped on tube at 1300° F.	Does not flash or burn.	Intermittent flashing and burning. Does not burn after leaving tube.
Molten Metal Ignition Test. Test fluid exposed to the surface of aluminum alloy at 1200° F., to test for spontaneous ignition.	Does not ignite: flashes by spark.	Does not ignite.

Fire-resistance Advantages of Pydraul

Pydraul fluids protect hydraulic equipment and personnel with *permanent* fire protection. Pydraul fluids contain no water to evaporate and leave a flammable residue. During their more than one billion machine hours of use, Pydraul fluids have been accidentally sprayed over molten metal, through electrical arcs, into flames and sparks —without causing fire. Pydraul fluids have never caused or contributed to a hydraulic fire in any type of equipment. They pass all of the important ignition tests for fire-resistance.

Monsanto introduced Pydraul F-9 as industry's first straight synthetic, fire-resistant hydraulic fluid. Pydraul F-9 rapidly became the standard against which all other synthetic hydraulic fluids were judged. Today, it is still considered the basis for comparison. Pydraul F-9 is now used in every major type of die-casting machine and a wide variety of other equipment found in the metal-working, glass, and process industries. No other fire-resistant hydraulic fluid has more on-the-line *proven* performance to offer.

Low viscosity Pydraul 60 flows freely at −20° F. It retains its properties and thermal stability at temperatures up to 200° F. In hydraulic operations that require precision flow *instantly,* Pydraul 60 supplies smooth operation from machine start to stop; it offers flow-on-demand operation without hydraulic lag. Pydraul 60 offers excellent, fire-resistant, hydraulic operation with vane, gear and piston pumps in high-speed machine tools.

0237408

TOWOLDMON0027620
WATER_PCB-00012089

PYDRAUL 150	PYDRAUL A-200	PYDRAUL 312	PYDRAUL 625
Cloudy Blue Liquid	Cloudy Blue Liquid	Blue Green Liquid	Cloudy Blue Liquid
1.119—1.135	1.415—1.430	1.100—1.115	1.340—1.360
0.17	0.80—1.10	0.30	0.30
0.15%	0.05%	0.10%	0.15%
145.9 SSU 52.5 SSU 163 SSU 56 SSU	144 SSU 35.7 SSU 204 SSU 48 SSU	312 SSU 50.9 SSU 346 SSU 56.5 SSU	625.7 SSU 45.9 SSU 845 SSU 59 SSU
−55° F.	+15° F.	−10° F.	+20° F.
3.13	2.28	2.74	2.66
200° F.	300° F.	225° F.	300° F.
617° F.	620° F.	615° F.	724° F.
0.00042	0.00040	0.00036	0.00040
0.40	0.28	0.36	0.28
0.072	0.068	0.069	0.065
0.1mm	0.2mm	0.1mm	0.09mm
319,000	438,000	365,000	375,000
Negligible	Negligible	Negligible	Negligible
Self-extinguishing.	Does not flash or ignite up to 3½ feet from orifice.	Intermittent flashing but self-extinguishing.	Does not flash or ignite up to 3½ feet from orifice.
Slight increase in flame intensity.	Slight increase in flame intensity.	Slight increase in flame intensity.	Very slight increase in flame intensity.
Intermittent flashing and burning. Little burning in pan below.	Does not flash or burn.	Intermittent flashing but does not propagate to pan below.	Does not flash or burn.
Does not ignite.	Does not ignite.	Does not ignite spontaneously. Flashes intermittently with ignition source.	Does not ignite.
Pydraul 150 is currently used in more than seven hundred G. P. E. (formerly Askania) regulators to control fuel-to-air ratios for blast furnaces, soaking pits, and other similar related equipment. Although developed especially for severe cold-weather, outdoor operations, Pydraul 150 is also used for certain missile-launch projects and in gears of LOX pumps located in oxygen-rich atmospheres at missile-fueling sites. Pydraul 150 also performs as an excellent low-viscosity fluid for high-speed machine tools.	Pydraul A-200 is one of the most widely used, general-purpose, fire-resistant hydraulic fluids in industry. Introduced in 1959, it was the first fire-resistant, straight synthetic hydraulic fluid to break the "price/performance barrier." Pydraul A-200 performs like premium-grade petroleum oil in a wide variety of industrial applications, from die-casting to aluminum extrusion. It protects plants and personnel with chemically "inherent" fire-resistence, yet costs less than other straight synthetic fluids.	The newest fire-resistant hydraulic fluid. A break through in medium viscosity fluids that offers high performance and lubricity at the lowest cost in the industry. Pydraul 312 hydraulic fluid is a unique marriage of synthetic fluids with specially chosen petroleum fractions. The result is a fire-resistant hydraulic fluid that matches or excels the properties of existing synthetic and water-containing fluids . . . even the "anti-wear" petroleum oils. Today, Pydraul 312 can be used in all major types of die casting machines, hydraulic presses, automatic welding machines, and injection molding equipment with excellent results.	High viscosity Pydraul 625 is tailored for ultra-heavy-duty hydraulic operations, such as for large industrial presses and pumps. Pydraul 625 is also used as a fire-and-explosion-resistant air compressor lubricant. Pydraul 625 can be used in any equipment requiring an 800 to 1000 SSU oil. Pydraul 625 has all the good performance characteristics that have won Pydraul fluids the reputation of quality and dependability throughout industry. In years of industrial field use, Pydraul 625 has proven to be a top-grade lubricant.

TOWOLDMON0027621
WATER_PCB-00012090

Pydraul Viscosities

Laboratory viscosity measurements of SSU (Saybolt Seconds Universal) are affected by fluid density. Because all petroleum oils used for hydraulic operations have similar densities, their measured viscosities can be compared; however, the densities of synthetic fluids differ from one another and from petroleum oils. To compare viscosities, measured viscosities of synthetic fluids must be corrected for density.

Each curve on the chart shows the viscosity-temperature relationship modified for the difference in density of the indicated Pydraul fluid. By comparing these curves with viscosity curves of light, medium, and heavy grades of petroleum oils, it can be seen that Pydraul fluids virtually duplicate viscosities of petroleum oils at normal operating temperatures.



Absolute Saybolt Viscosity = Measured SSU × Density of Pydraul

Pydraul Lubrication Properties

Pydraul fluids lubricate as well as premium petroleum oil. Because of this premium lubricity, Pydraul fluids give the same long pump life as premium petroleum oil. Equipment responds at its optimum capability. And Pydraul fluids are designed to be permanent — they never evaporate or wear out.

	PYDRAUL F-8	PYDRAUL 60	PYDRAUL 150	PYDRAUL A-200	PYDRAUL 312	PYDRAUL 625
Timken Load (Passing)	50 lbs. 17,500 psi	14 lbs. 7,400 psi	40 lbs. 18,200 psi	50 lbs. 16,300 psi	55 lbs. 18,000 psi	55 lbs. 21,200 psi
Almen Wear	2.0 mg@ 4,000 psi	——	3.9 mg@ 4,000 psi	1.3 mg@ 4,000 psi	——	2.2 mg@ 4,000 psi
Almen Load	43 lbs. 25,000 psi	48 lbs. 25,000 psi	46 lbs. 23,000 psi	44 lbs. 24,000 psi	——	50 lbs. 23,000 psi
Falex Load—Jaw Load—lbs.	4100	2300	2000	4200	1800	4100
—Torque—lb. inches	93	73	64	90	35	89
Falex Wear (Under continuous load @ 100 lbs., loss in inches)						
1st 10 minutes	0.000428	0.000475	0.000428	0.000380	——	0.000618
2nd 10 minutes	0.000190	0.000380	0.000332	0.000380	——	0.000332
Shell Four-Ball Wear (167°F. 1 hr., 830 rpm, mm scar) Steel on Steel						
10 kg.	0.28	0.27	0.36	0.29	0.25	0.26
40 kg.	0.67	0.48	0.51	0.43	0.44	0.62
Steel on Bronze						
10 kg.	1.18	0.82	0.80	1.40	0.87	1.10
40 kg.	1.28	2.35	1.58	1.70	——	1.19
Pump Test—Vickers (V-105-E, 140°F. 1000 hrs.)						
Ring, grams (loss or gain)	−0.0084	−0.0037	−0.1212	−0.0848	−0.0013	−0.0013
Vanes, grams (loss or gain)	−0.0011	−0.1859	−0.0378	−0.0191	−0.0021	−0.0015
Bushing 2015 grams (loss or gain)	+0.0120	+0.0008	−0.1601	−0.0151	+0.0081	−0.0045
Bushing 2016 grams (loss or gain)	−0.0063	−0.0020	−0.1134	−0.0217	−0.0057	−0.0050

0237410

TOWOLDMON0027622
WATER_PCB-00012091

Mixing Compatibility

PYDRAUL WITH OTHER HYDRAULIC FLUIDS

	F9	60	150	200	312	625
CELLULUBE						
90	**NO**	YES	**NO**	YES	**NO**	YES
150	**NO**	YES	**NO**	YES	**NO**	YES
220	**NO**	YES	**NO**	YES	**NO**	YES
300	**NO**	YES	**NO**	YES	**NO**	YES
550	**NO**	YES	**NO**	YES	**NO**	YES
HOUGHTO-SAFE						
1010	**NO**	YES	**NO**	YES	**NO**	YES
1055	**NO**	YES	**NO**	YES	**NO**	YES
1120	**NO**	YES	**NO**	YES	**NO**	YES
1130	**NO**	YES	**NO**	YES	**NO**	YES

PYDRAUL WITH OTHER PYDRAULS

F9	—	**NO**	YES	YES	YES	YES
60	**NO**	—	**NO**	YES	**NO**	YES
150	YES	**NO**	—	YES	YES	YES
200	YES	YES	YES	—	YES	YES
312	YES	**NO**	YES	YES	—	YES
625	YES	YES	YES	YES	YES	—

WATER-GLYCOL and **WATER-OIL EMULSION** Fluids — Pydraul hydraulic fluids are not compatible with these fluids.

Handling and Storage

As with all specialized industrial fluids, certain precautions are advisable when handling Pydraul fluids. No problems will arise when Pydraul fluids are used as recommended.

Avoid repeated or continuous skin contact. Repeated or prolonged contact can lead to drying and skin "chapping." Where prolonged skin contact cannot be avoided, gloves should be worn.

At room temperatures, there is no vapor inhalation hazard from Pydraul; however, inhalation of vapors at high temperatures should be prevented. In extensive animal experimentation, exposures to vapors for one hour showed local respiratory irritation, although no systemic effects were produced.

Although eye irritation studies using Pydraul at full strength indicate Pydraul is a mild irritant, there is no evidence to show Pydraul causes permanent damage to eye tissues. If Pydraul fluid is splashed or sprayed into the eyes, eyes should be thoroughly flushed with water and the workman referred to a physician. To relieve irritation, physicians have used 1% pontocaine solution, as well as the ophthalmic cortisone acetate solution.

Pydraul hydraulic fluids can be stored at sub-zero temperatures without fluid damage. Before using, simply allow the fluid to warm to room temperature. Drums stored outside should be sealed tightly and placed in a horizontal position to keep out moisture.

TOWOLDMON0027623
WATER_PCB-00012092

DISTRICT SALES OFFICES
ALL DIVISIONS

ATLANTA, GEORGIA 30326
Lenox Towers West,
3390 Peachtree Rd. N.E.
Tel. (404) 231-4320

BOSTON, MASSACHUSETTS 02149
Everett Station
Tel. (617) Dunkirk 7-5010

CHICAGO, ILLINOIS
3158 Des Plaines Ave.
Des Plaines, Illinois 60018
Tel. (312) 296-6688

CINCINNATI, OHIO 45206
1501 Madison Road
Tel. (513) 751-6707

CLEVELAND, OHIO 44122
3645 Warrensville Center Rd.
Tel. (216) 991-5400

DETROIT, MICHIGAN 48235
600 Northland Towers
Tel. (313) 357-0910

HOUSTON, TEXAS 77002
1300 Main Street
Tel. (713) Capitol 3-4011

LOS ANGELES, CALIFORNIA 90022
6670 E. Flotilla St.
Tel. (213) Raymond 3-2492

MINNEAPOLIS, MINNESOTA 55402
912 Northstar Center 110 S. Seventh St.
Tel. (612) Federal 9-4651

NEW YORK, NEW YORK 10017
277 Park Avenue
Tel. (212) 922-4111

PITTSBURGH, PENNSYLVANIA 15222
No. 4 Gateway Center Bldg. Room 1406
Tel. (412) 261-2156

ST. LOUIS, MISSOURI 63166
800 N. Lindbergh Blvd.
Tel. (314) Wydown 3-1000

SAN FRANCICSO BAY AREA
2710 Lafayette, Santa Clara, Calif. 95052
Tel. (408) 243-0414

SEATTLE, WASHINGTON 98104
911 Western Avenue
Tel. (206) Main 2-4203

SPRINGFIELD, MASSACHUSETTS 01101
730 Worcester Ave.
Tel. (413) 788-6911

WILMINGTON, DELAWARE 19803
2005 Concord Pike, Fairfax
Tel. (302) Olympia 6-6531

Additional District Offices are maintained by:

Agricultural Division

EL DORADO, ARKANSAS 71731
Smackover Highway
P. O. Box 231
Tel. (501) Union 3-3151

LULING, LOUISIANA 70070
P. O. Box 174
Tel. (504) 784-2911

Building Products Department

ST. LOUIS, MISSOURI 63166
800 N. Lindbergh Blvd.
Tel. (314) Wydown 3-1000

LOS ANGELES, CALIFORNIA 90066
814 San Fernando Road
Tel. (213) CA. 2-9111

Chemstrand Company Division

AKRON, OHIO 44313
3030 West Market St.
Tel. (216) Temple 6-7941

CHARLOTTE, NORTH CAROLINA 28202
Wachovia Bank Building
129 West Trade St.
Tel. (704) 376-9871

NEW YORK, NEW YORK 10001
350 Fifth Ave.
Tel. (212) 556-5100

ENGLEWOOD CLIFFS, N. J.
661 Palisades Ave.
Englewood Cliffs, New Jersey 07631
Tel. (201) 568-2151

Hydrocarbons & Polymers Division Lion Oil

EL DORADO, ARKANSAS 71730
Lion Oil Building
Tel. (501) Union 3-3111

JACKSON, MISSISSIPPI 39209
P. O. Box 10937
Westland Station
Tel. (601) Fleetwood 2-3648

LITTLE ROCK, ARKANSAS 72203
1515 West Seventh St.
Tel. (501) Franklin 6-2437

MEMPHIS, TENNESSEE 38101
1023 Riverside Drive
P. O. Box 252
Tel. (901) Whitehall 8-4451

Organic Chemicals Division
(Rubber Industry)

AKRON, OHIO 44311
920 Brown Street
P. O. Box 2307
Tel. (216) Hemlock 4-1921

MONSANTO, 800 N. LINDBERGH BLVD., ST. LOUIS, MISSOURI 63166

0237412

2-2131-0466-6 LITHO IN U.S.A.

TOWOLDMON0027624
WATER_PCB-00012093

0237413

MONSANTO, 800 N. LINDBERGH BLVD., ST. LOUIS, MISSOURI 63166

Monsanto

TOWOLDMON0027625
WATER_PCB-00012094