

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-788 LOT 34863

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

<u>50</u>	<u>67</u>	<u>3,350</u>		

STUMP

TOTAL NET WT. 3,350 PKG. N-CODE 1130

PROD. SPVR. WPP DATE 31 55 WHSE. OPER.

N 27535

22
240
CG 03 CODE KY-788-D PKG.
MAR 13 34863
EST. WGT. 960 860 LBS.

O.K
BAGS
3460

Total Wgt. 3560# Req()

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-788-D (0)	APPROVED BY EWK 9/22/76
	DCG 9/27/76
TYPED BY NE 2/17/77	
MAKING NOTES	

REMARKS

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS					-PRESSING-		RECORD				
VAT	240				PRESSLOAD		1ST	2ND	3RD	4TH	5TH
DATE	3-13-80				STARTED		8 AM				
TIME	7:45 AM				CAKES USED		16				
RELEASED BY	(30)				WATER ON		12:30 PM				
PRESS	22	23	24		HRS. WASHED		5				
NO. OF CAKES	46	46	46		OHMS		3000				
PRESS With					HRS. WASHED						
WASH TO 2000					OHMS						
TEST AFTER 2					HRS. WASHED						
LOAD ON 5 CAPS					OHMS						
					CAKE CONDITION		7				
					NO. CARS LOADED						
					EXPLAIN LOSSES						

SAMPLES 1- 8oz JAR
DELIVER TO CTL for Color

SAMPLED BY 4469 RELEASED BY ALK

-DRYING-

Dry 12 hrs at 220 °F L.V.
Then Dry 8 hrs at 160 °F

LUMP - OK - WET - SALTS - CONTAMINATED
No Record of any Processing Loss

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

No Drums 15
NO. CARS PULLED
LUMP WGT. 3336
SAMPLED BY
RELEASED BY ALL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

.00 T
348.53 #
.41 #
2.94 #
.00 T
2.56
.14 -
2.42
.14 -
2.50
.14 -
2.35
.14 -
2.42
.14 -
2.45
.14 -
2.51
.14 -
2.53
.14 -
2.56
.14 -
2.44
.14 -
2.46
.14 -
2.41
.14 -
2.37
.14 -
2.28
.14 -
1.20
.14 -
333.6 T