

VISCOSITY WORK SHEET

Item <u>1593</u>	P.T.No.	Date <u>4/23/54</u>
Worker <u>Jackie Harrison</u>	Polymer <u>Polymer M</u>	Solvent <u>M-Cresol</u>
For <u>Brebnr</u>	Charge <u>1216</u>	Temperature
Viscometer No. <u>735</u>	Efflux Time <u>156.5</u>	Weight: Gross
Viscometer No. <u>370</u>	Efflux Time <u>150.8</u>	Tare
Viscometer No.	Efflux Time	Net <u>0.1562</u>

		Visc.	Solution	Efflux Times	Rel. Visc.	Inh.visc. or M.W.
Sample	Flask No.	No.				
4186-105-B	M 18	735	273.1,	273.1	1.743	1.16
	909	370	247.2,	247.3, 247.3	1.640	1.13
	mld #1		25.3747 <u>25.3687</u> 0.0060	.1250 <u>.0060</u> .1190 <u>.4760</u>		
	909 #2		28.4976 <u>28.4819</u> 0.0157	.1250 <u>.0157</u> .1093 <u>.4372</u>		