

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-908 LOT 34031

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1764</u>	<u>1</u>	<u>T-797</u>		
<u>1756</u>	<u>1</u>	<u>T-230</u>		

STUMP

TOTAL NET WT. 3520 PKG. N-CODE _____PROD. SPVR. 911 DATE 2/2/80 WHSE. OPER. _____

23/204
CG 03 CODE KY-908-D PKG.
→ JAN 26 34031
EST. WGT. 949 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-908-D (E) Alternate	APPROVED BY EWK 12/12/77 DCG 12/14/77
TYPED BY rj 2/14/78	

MAKING NOTES

REMARKS

Total Wgt. 3549 #

NAME: Krolor® Yellow - Light

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT		244				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		1-27-80				STARTED	2:30 PM				
TIME		12:50				CAKES USED	46				
RELEASED BY		K.H.				WATER ON	2 Hrs				
PRESS	2	22	23	24		HRS. WASHED	4 HRS				
NO. OF CAKES	46	46	46	52		OHMS	2000				
PRESS with		AGITATION				HRS. WASHED					
WASH TO	2000	OHMS	with 135-145°F water			OHMS					
TEST AFTER	2	HOURS				HRS. WASHED					
LOAD	on 6 cars					OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES 8oz Jar
DELIVER TO Ctl for color

SAMPLED BY HBS RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 11
LUMP WGT. 3558
RELEASED BY

-GRINDING-

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170 °FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

34031
41
158

0.00 *
3.53 +
0.12 -
3.40 +
0.12 -
3.40 +
0.12 -
3.47 +
0.12 -
3.42 +
0.12 -
3.30 +
0.12 -
3.34 +
0.12 -
3.42 +
0.12 -
3.45 +
0.12 -
3.20 +
0.12 -
2.97 +
0.12 -
35.58 *