MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE PT 284 LOT 1-1530

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	16	2731		
	STUMP			

TOTAL NET WT. 2731 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
	5/30/81	213

0.T

176.+
138.+
170.+
167.+
172.+
171.+
170.+
165.+
164.+
130.+
152.+
174.+
178.+
178.+
136.+
130.+
2731.T

DUP050097372

FINISHING Note: CO-PULY WITH N-65-A & MFS

CG 20 CODE BT-284D PKG. ____
→ E 1580
EST. WGT. 2362 LBS.

6 And 9
Bldg

MFS

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
TYPED BY	

MAKING NOTES

REMARKS

NAME: MONASTRAL & BLUE B

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED					
TIME						CAKES USED					
RELEASED BY						WATER ON					
PRESS						HRS. WASHED					
NO. OF CAKES						OHMS					
PRESS		AGITATION				HRS. WASHED					
WASH TO		OHMS				OHMS					
TEST AFTER		HOURS				HRS. WASHED					
LOAD PANLOAD						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED	7				
						EXPLAIN LOSSES					
SAMPLES											
DELIVER TO						SAMPLED BY		RELEASED BY BLL			

-DRYING-

HOURS	L.V.	H.V.	LUMP: - OK - WET - SALTS - CONTAMINATE
TEMP.	°F	°F	
DRY 20 HRS AT 220°F			Color appears dry.
			ADDITIONAL DRYING HOURS REQUIRED
			16
SAMPLES			NO. CARS PULLED LUMP WGT. 2596
DELIVER TO			SAMPLED BY RELEASED BY [signature]

-GRINDING-

MILL 7 OR 8 LSP 3/32" PP SCREEN 1785 RPM	SCREEN RPM
MAX. TEMP. 150 °F	MAX. TEMP. °F
CO-PULY WITH 150# N-65-A	
	EXPLAIN LOSSES
SAMPLE AFTER / [redacted] MIXING	DATE MIXED 5/29/81
SAMPLES ENV + 2 PINTS	

DUP050097373

CG 20 CODE BT-284-D PKG. E1580

→ MAY 20 1987

EST. WGT. _____ LBS.

NOTE: MAKING — FILL IN EST WGT FROM BATCH CARD

PROCESSING INSTRUCTIONS: BATCH UN

PROCESSES	APPROVED
BT-284-D (P	AJC 05 10 7
	DCG 07 12 7
TYPED BY	
emw070279	

MAKING NOTES

REMARKS

NAME. MONASTRAL® BLUE B — NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

CAT				
DATE				
TIME				
RELEASED BY				
PRESS	9 + 10	17 + 18		
NO. OF CAKES	2 x 119 + 43	3 x 84 + 28		

PRESS with AGITATION

WASH TO _____ OHMS

TEST AFTER _____ HOURS

LOAD on 8 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5
STARTED					
CAKES USED					
HRS TO FILL					
CAKE CONDITION					
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

—DRYING—

Dry 18 hrs at 220°F

LUMP: — OK — WET — SALTS — CONTAMINA

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT.

SAMPLED BY RELEASED BY

—GRINDING—

MILL 7 or 8 LSP 3/32" RP SCREEN 1785 RPM

MAX. TEMP. 200 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050097374





DUP050097375