

MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE [illegible] LOT [illegible]

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	[illegible]	[illegible]	[illegible]	
[illegible]	STUMP			

TOTAL NET WT. [illegible] PKG. N-CODE

PROD. SPVR. [illegible] DATE [illegible] WHSE. OPER. [illegible]

N 31916

12

260 CG 40 CODE RT-539-D PKG. ____

→ FEB 14 34354

EST. WGT. 486 LBS.

29

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-539-D (N)	EWK 10-25-
	DCG 10-25-
TYPED BY	
jlc 11-15-77	

MAKING NOTES

REMARKS

NAME: NAPHTHANIL® RED DARK

BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT	260					PRESSLOAD	1ST	2ND	3RD	4TH	5T
DATE	2-15-80					STARTED	830 Am				
TIME	8001 Am					CAKES USED	36				
RELEASED BY	Atm					WATER ON	12 PM				
PRESS	12					HRS. WASHED	9				
NO. OF CAKES	36					OHMS	4000				
PRESS	WITHOUT	AGITATION				HRS. WASHED					
WASH TO	4000	OHMS WITH 35-75°F WATER				OHMS					
TEST AFTER	4	HOURS				HRS. WASHED					
LOAD	ON 3 CARS					OHMS					
						CAKE CONDITION	3				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

HOURS DRY 20 HRS AT 180°F L.V. H.V.

TEMP. °F °F

LUMP: - OK - WET - SALTS - CONTAMINAT

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS: 4

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT. 490

RELEASED BY

-GRINDING-

MILL #5 LSP 1/8" RP SCREEN 1750 RPM

MAX. TEMP. 170 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES CO2 USAGE 8-8-8 %

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 Env

DELIVER TO C T L

DATE MIXED

SAMPLED BY 297

2/26/80 RELEASED BY

N 31916.01

DUP050292781



N 31916.02

DUP050292782