

REPRODUCED AT THE NATIONAL ARCHIVES

OPA 26008

N 4406

BRAND NAME	INGREDIENTS	FORMULA IN LBS		YIELD IN GALS		UNIT COST PER POUND OR GAL	
		Before Change	After Change	Before Change	After Change	Before Change	After Change
SUPER OUTSIDE WHITE	Ti-Sil	255	255	9.8	9.8	.0575	.0575
	35% Lead Zinc	357	357	7.3	7.3	.07	.07
	White Lead Carbonate	179	179	3.2	3.2	.0825	.0825
	Refined L O	418.5	209.25	54	27	.161	.161
	Bodied L O Z-6	-----	83.7	-----	9.3	-----	.171
	Mineral Spirits	-----	125.6	-----	19.3	-----	.017
	Liquid Driers	41.25	41.25	5.5	5.5	.0677	.0677
	Calculated Yield	1250.75	1250.8	79.8	80.4	-----	-----
	Material Cost Per Gal	-----	-----	-----	-----	-----	-----
	L O Content per Gal	-----	-----	-----	-----	-----	-----
CHILTON OUT* SIDE WHITE	Zinc Oxide	400	400	8.5	8.5	.0725	.0725
	White Lead Carbonate	410	410	7.3	7.3	.0825	.0825
	Asbestine	150	150	6.5	6.5	.01	.01
	Refined L O	589	299.5	76.0	38.3	.161	.161
	Bodied L O Z-6	---	93.2	---	11.73	---	.171
	Mineral Spirits	---	150.5	---	23.1	---	.017
	Liquid Driers	52.5	75.0	7.0	10.0	.0677	.0677
	Calculated Yield	1601.5	1578.5	105.3	105.4	-----	-----
	Material Cost Per Gal	-----	-----	-----	-----	-----	-----
	L O Content per Gal	-----	-----	-----	-----	-----	-----