

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 4C-16-B LOT E1339

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

50643200

STUMP

400 2200

TOTAL NET WT.

3200

PKG. N-CODE

1102

PROD. SPVR.

DATE

WHSE. OPER.

4/65 15 1981

93
42

CG 01 CODE YC-16-B PKG. 93
MAY -0-81-E1339
EST. WGT. 3130 LBS.

*Red
HP*

PROCESSING INSTRUCTIONS: BATCH UNIT

(A) YC-16-B	APPROVED BY
	AJC 4-1-75
	JFH 5-5-75
	DCG 5-14-75
TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS						-PRESSING-		RECORD					
AT	242					PRESSLOAD	1ST	2ND	3RD	4TH	5TH		
DATE	5-12-81					STARTED	6:30						
TIME	6:00					CAKES USED	32						
RELEASED BY						WATER ON	10A						
PRESS		92	93	2	25	HRS. WASHED	3						
NO. OF CAKES	42	32	32	32	32	OHMS	2000						
PRESS		AGITATION				HRS. WASHED							
WASH TO	2000	OHMS				OHMS							
TEST AFTER	2	HOURS WITH 35-75 F WATER				HRS. WASHED							
LOAD ON 4 CARS						OHMS							
						CAKE CONDITION							
						NO. CARS LOADED	4						
						EXPLAIN LOSSES							

SAMPLES													
DELIVER TO								SAMPLED BY		RELEASED BY	BL		

-DRYING-

DRY	16 HOURS AT	220 F	LUMP: - OK - WET - SALTS - CONTAMINATED
			DRYER SECTIONS USED:
			<i>No record of any processing found. Could possibly be mixed with lot YC-12-1340 over 40000</i>
			ADDITIONAL DRYING HOURS REQUIRED

SAMPLES								NO. DRUMS	10
DELIVER TO								NO. CARS PULLED	2726
								SAMPLED BY	
								RELEASED BY	PH

-GRINDING-

MICROATOMIZE	SCREEN	RPM
SET ROOF GATE AT 5 INCHES AIR FLOW	MAX. TEMP.	°F
MAGNETIC READING ON ATOMIZER PANEL 1.0"	EXPLAIN LOSSES	
		<i>Note dr. wgt. on back of card</i>
SAMPLE	WITHOUT MIXING	DATE MIXED
SAMPLES 1 ENV		
DELIVER TO	CT L	SAMPLED BY
		RELEASED BY

1339
41
231

0.00 *

3.19 +
0.12 -
3.07 +
0.12 -
2.91 +
0.12 -
3.16 +
0.12 -
3.25 +
0.12 -
14.98 >

1339
41
16

0.00 *

14.98 +
3.14 +
0.12 -
3.03 +
0.12 -
3.21 +
0.12 -
2.96 +
0.12 -
0.34 +
0.12 -
27.26