

TO: R. W. Daasch

CC: T. G. Townsend
George Otto
M. Paulson
G. Weaver
R. Jimenez

 MAYTAG
PROCESS ENGINEERING
ANALYSIS REPORT

Form No. 186-22C

Analysis No. 89 1467 Project No. - File 1989

Date Rec'd 7-21-89 Requested by R. W. Daasch CC 2910

Sample Description: Compound 03162X-2 for part 9-1403 Door Gasket -
Type PVC 4341

Reason for Analysis: Trial sample from Chardon Rubber

ANALYSIS

Date of Analysis 7-26-89

	<u>Analysis</u>	<u>Specification</u>
Tensile strength, psi	1926	1575
Durometer, Shore A	73	65-74
Volatile Loss, %	1.0	1.0 Max.
Specific gravity	1.30	1.25-1.29

CHARDO 01088