

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE VE-735-D LOT A-514

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

50 78 _____

_____ STUMP 4091 _____

TOTAL NET WT. 39 00 PKG. N-CODE 1000

PROD. SPVR _____ DATE _____ WHSE. OPER. _____

1/14 1-27-82 _____

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YE-735-D PKG

PROCESSES APPROVED BY
YE-735-D (M) FWP 10/07/81
ALTERNATE
TYPED BY JMM

LOT A2K14

EST. WT. 3819* LBS.

MAKING NOTES

JOB NAME: 01YE735DPM

=====

INSTRUCTIONS		= PRESSING =	RECORD				
VAT			1ST	2ND	3RD	4TH	5TH
DATE	24/11	PRESSLOAD	1230				
TIME	11:40	STARTED	42				
RELEASED BY	WB	CAKES USED	400				
PRESS	2 (91)	WATER ON	8				
NO. OF CAKES	32 (42)	HRS. WASHED	214				
PRESS WITH AGITATION SEE BELOW		M MHOS					
WASH TO 285 M MHOS WITH 35-75°F		HRS. WASHED					
WATER.		M MHOS					
TEST AFTER 2 HOURS.		HRS. WASHED					
LOAD ON 5 CARS.		M MHOS					
STOP AGITATOR AT ABOUT 50°		CAKE CONDITION					
DO NOT EXTRUDE.		NO CARS LOADED	5				
		EXPLAIN LOSSES					

=====

SAMPLES JAR
DELIVER TO

SAMPLED BY
RELEASED BY

=====

= DRYING =

DRY 14 HRS AT 240°F MAY 1 - AUG. 31. LUMP: - OK - WET - SALTS - CONTAMINATED

DRY 12 HRS AT 240°F SEPT. 1 - APR 30

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS / 3
LUMP WGT 4091

=====

= GRINDING =

MIKROATOMIZE

SET ROOF GATE AT 5 INCHES AIR FLOW.

MAGNEHELIC READING ON ATOMIZER PANEL
BOARD (1.0")

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 2 PT. CANS
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY



11
412
0
323
14
325
12
316
12
354
12
335
12
321
12
327
12
352
12
321
12
350
12
317
12
356
12
232
12
4011