

11/15/82

PRODUCT NAME: MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YC-16-B PKG _____

PROCESSES
YC-16-B (C)

APPROVED BY:
FWP 09/22/81

LOT **L2K56**

COMTYP JOB NAME: 01YC016BPC

4138

EST. WT. ~~309B~~* LBS.

MAKING NOTES: _____

INSTRUCTIONS						= PRESSING =	RECORD								
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 500 M MHOS WITH 35-75* WATER	TEST AFTER 2 HOURS	LOAD ON	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
										STARTED					
										CAKES USED					
										WATER ON					
										HRS. WASHED					
										M MHOS					
										HRS. WASHED					
										M MHOS					
										HRS. WASHED					
										M MHOS					
										CAKE CONDITION					
										NO CARS LOADED					
										EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

- DRY 16 HOURS AT 220* F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

= GRINDING =

MIKROATOMIZE
SET ROOF GATE AT 2 INCHES AIR FLOW
SET LUMP FEED SCREW AT 1/2 SPEED
MAGNEHELIC READING ON ATOMIZER
PANEL 1.0"

SCREEN
MAX. TEMP.
RPM
F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

68
41
324

0.00 *

3.43 +

0.14 -

3.47 +

0.14 -

3.51 +

0.14 -

3.38 +

0.12 -

3.29 +

0.12 -

3.35 +

0.12 -

3.36 +

0.12 -

3.55 +

0.12 -

3.59 +

0.12 -

3.13 +

0.12 -

32.80 *

0.00 *

68
41
85

0.00 *

3.89 +

0.12 -

3.35 +

0.12 -

1.57 +

0.12 -

32.80 +

41.25 *