

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-787LOT 34640

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>1730</u>	<u>1</u>	<u>T</u>	<u>130</u>	
<u>1690</u>	<u>1</u>	<u>T</u>	<u>262</u>	
STUMP				

TOTAL NET WT. 3420 PKG. N-CODE _____PROD. SPVR. SMDATE 3,7,80

WHSE. OPER. _____

N 26284

DUP050093689

CG 03 CODE KY-787-D PKG. _____

→ MAR-1 34540

EST. WGT. 1090 990 LBS.

TOTALS

OK
KP

Total Wgt. 3490# 3390

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (R)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NE 2/12/77	
MAKING NOTES	

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT		240			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		9-4-86			STARTED	7 PM				
TIME		7:00 PM			CAKES USED	46				
RELEASED BY					WATER ON	7:30 AM				
PRESS	22	23	24	24	HRS. WASHED	2				
NO. OF CAKES	46	46	46	52	OHMS	2.222				
PRESS with		AGITATION			HRS. WASHED					
WASH TO 2000		OHMS with 35-75°F water			OHMS					
TEST AFTER 2		HOURS			HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION	6				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY #469 RELEASED BY

-DRYING-

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3425
RELEASED BY

-GRINDING-

MILL 039 HSP 3/32" BP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 Pt. can
DELIVER TO CTL

DATE MIXED
SAMPLED BY

RELEASED BY

DUP050093690

N 26284.01

34640
124
41

2.47 +
0.14 -
2.62 +
0.14 -
2.59 +
0.14 -
2.42 +
0.14 -
2.49 +
0.14 -
2.70 +
0.14 -
2.50 +
0.14 -
2.55 +
0.14 -
2.53 +
0.14 -
2.53 +
0.14 -
2.57 +
0.14 -
2.61 +
0.14 -
2.50 +
0.14 -
2.51 +
0.14 -
0.76 +
0.14 -
34.25 *

1
15. DRUM
]