CODE 42.16 LOT 21855

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	65	3250		
STUMP	Stump	3250		

TOTAL NET WT. 3250 PKG. N–CODE 1-0-0-0

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	3/13/81	

93
342

BG 01 CODE YC-16-B PKG. 93

→ MAY -0·81- E1235

EST. WGT. 3130 LBS.

OK FF

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(A) YC-16-B	A.C 4-7-75
	JFH 5-5-75
	DCG 5-14-75
TYPED BY	

MAKING NOTES

REMARKS

NAME: MOLYBDATE ORANGE — NON-BLEEDING

E

INSTRUCTIONS — -PRESSING- — RECORD

VAT	342					
DATE	5.8					
TIME	1:30 PM					
RELEASED BY	JCB					
PRESS	91	92	93	2	25	
NO. OF CAKES	42	32	32	32	32	

PRESS — AGITATION

WASH TO 2000 — OHMS

TEST AFTER 2 — HOURS WITH 35-75 F WATER

LOAD ON 4 CARS

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	3 AM				
CAKES USED	34				
WATER ON	7:15				
HRS. WASHED	2 3/4				
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				

EXPLAIN LOSSES

SAMPLES

DELIVER TO

SAMPLED BY — RELEASED BY

-DRYING-

DRY 16 HOURS AT 220 F

LUMP: - OK - WET - SALTS - CONTAMINATED

DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES

DELIVER TO

NO. CARS PULLED — LUMP WGT. 3332

SAMPLED BY — RELEASED BY

-GRINDING-

MICROATOMIZE

SET ROOF GATE AT 5 INCHES AIR FLOW

MAGNEHELIC READING ON ATOMIZER PANEL 1.0"

SCREEN — RPM

MAX. TEMP. — °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 ENV

DELIVER TO C T L

DATE MIXED

SAMPLED BY — RELEASED BY

DUP050096111

1235
4100
158

0.00 *

3.05 +
0.12 -
2.94 +
0.12 -
2.89 +
0.12 -
2.97 +
0.12 -
3.00 +
0.12 -
3.06 +
0.12 -
2.95 +
0.12 -
3.07 +
0.12 -
3.08 +
0.12 -
2.95 +
0.12
2.97 +
0.12 -
1.83 +
0.12 -
33.32 *

DUP050096112