

1 DRY AND PASTE ONLY

LOT

NO. PKG

PACK. WGT**LOCATION**

PQ

TOTAL NET WT.

PKG. N-CODE

PROD. SPVR.

DATE _____

WHSE. OPER.

PRODUCT NAME: MOLYBDATE ORANGE

NON-BLEEDING

10/06/82

CG 01 CODE YC-16-B PKG _____

PROCESSES
YC-16-B (C)

APPROVED BY:
FWP 09/22/81

LOT **K2J88**

COMTYP JOB NAME: 01YC016BPC

EST. WT: 3098* LBS.

MAKING NOTES: _____

INSTRUCTIONS

= PRESSING =

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF Cakes	PRESS WITH AGITATION	WASH TO 500 M MHOS WITH 35-75* WATER	TEST AFTER 2 HOURS	LOAD ON 4 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	HRS. WASHED	M MHOS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
				91	42																	
				92	32																	

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 16 HOURS AT 220* F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 3318

= GRINDING =

MIKROATOMIZE
SET ROOF GATE AT 2 INCHES AIR FLOW
SET LUMP FEED SCREW AT 1/2 SPEED
MAGNEHELIC READING ON ATOMIZER
PANEL 1.0*

SCREEN
MAX. TEMP. RPM
F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

88
124
41

*5000.00
12.00*

2.86 +
0.12 -
2.93 +
0.12 -
2.93 +
0.12 -
3.06 +
0.12 -
3.11 +
0.12 -
3.04 +
0.12 -
3.01 +
0.12 -
2.90 +
0.12 -
3.11 +
0.12 -
3.07 +
0.12 -
2.93 +
0.12 -
1.59 +
0.12 -
33.18 *