O'BRIEN

WEATHER KING®

Latex HOUSE PAINT

A20-08 WOOD PRIMER (Latex)

NET 128 FL. OZ. (1 GAL.)

WEATHER KING LATEX EXTERIOR PRIMER

(For Unpainted Wood Surfaces)

Weather King Latex Exterior Primer may be used over unpainted wood siding and trim, and wood shingles. As an undercoater for Weather King Latex House Paint, this primer makes possible an ALL-LATEX SYSTEM for exterior wood surfaces. Resists grain checking, provides blister resistant properties, eliminates fire hazard. Clean up with soap and water.

DIRECTIONS

Preparation — Remove dirt, chalk, and loose paint. Repair flashings, caulk and provide adequate ventilation for release of moisture. Sand under eaves and protected areas, **wash with detergent and thoroughly rinse.**

Tinting — Tint toward the finish color with **lead-free, sun-proof** Tone-All Universal Tinting Colors. DO NOT TINT WITH OIL COLORS or intermix with other paints.

Application — Apply when temperature is 50° F. or above. Flow on liberally with a nylon brush. Do not spread at a rate more than 300 square feet per gallon. Some woods containing water-soluble dyes, such as western red cedar and redwood, may require two primer coats to prevent "bleeding." Staining within minutes of the first coat application indicates the need for a second primer coat. Sand rough sawed lumber between primer coats to eliminate wood fiber "wicks" that carry dyes into the top coat. Thinning is not necessary. Clean tools with water. Dries in 1 hour. Recoat same day.

NOTE: Weather King Latex Exterior Primer may be used as an undercoater for conventional oil house paints also. — (WWP)

KEEP FROM FREEZING

CAUTION — CONTAINS LEAD. HARMFUL IF SWALLOWED.
Do not take internally. Do not apply on window sills, toys, furniture or interior surfaces of rooms which may be used by children. Close container after each use. KEEP OUT OF THE REACH OF CHILDREN. 94

SINCE O'BRIEN 1875

THE O'BRIEN CORPORATION · SOUTH BEND, IND. 46621

BALTIMORE, MD. • OKLAHOMA CITY, OKLA. • LOS ANGELES, CAL. • SAN FRANCISCO, CAL. • BRUNSWICK, GA.

49 TOC 001820